The Photodegradation Effect of Organic Dye for Metal Oxide (Cr₂O₃, MgO and V₂O₃) Treated CNT/TiO₂ Composites

Ming-Liang Chen, Jang-Soon Bae,[†] Hee-Seung Yoon,[‡] Chang-Sung Lim, and Won-Chun Oh*

Department of Advanced Materials Science & Engineering, Hanseo University, Chungnam 356-706, Korea

*E-mail: wc_oh@hanseo.ac.kr

[†]Department of Engineering and Chemical Technology, Dankook University, Chungnam 330-714, Korea

[‡]Department of Chemical Engineering, Chungnam National University, Yuseong, Daejeon 305-764, Korea

Received November 22, 2010, Accepted December 28, 2010

Three kinds of organometallic compounds (chromium acetylacetonate, magnesium acetate and vanadyl acetylacetonate) were used as transition metal precursor, titanium *n*-butoxide and multi-walled carbon nanotube as titanium and carbon precursor to prepare metal oxide-CNT/TiO₂ composites. The surface properties and morphology of metal oxide-CNT/TiO₂ composites were by Brauer-Emmett-Teller (BET) surface area measurement, scanning electron microscopy (SEM), transmission electron microscopy (TEM), X-ray diffraction (XRD) and energy dispersive X-ray (EDX) analysis. The photocatalytic activity of prepared metal oxide-CNT/TiO₂ composites was determined by the degradation effect of methylene blue in an aqueous solution under irradiation of visible light.

Key Words : MWCNT, Transition metals, TEM, Photocatalytic activity

Introduction

The degradation of organic pollutants in waste water by photocatalysis, using the wide optical band gap material (TiO₂), has attracted extensive attentions during recent 20 years.^{1,2} However, it has been well known that this type of photo-oxidation has two typical drawbacks: firstly TiO₂ is a high energy band ($E_g \approx 3.2$ eV) material that can only be excited by high energy ultraviolet irradiation with a wavelength of no longer than 385 nm. This practically rules out the use of sunlight as an energy source for the photo-reaction. Secondly, a low rate of electron transfer to oxygen and a high rate of recombination between excited electron-hole pairs result in a low quantum yield rate and also a limited photo-oxidation rate.³ Recently, many studies have been done to improve photocatalytic properties of TiO₂ powders by doping using transition metal elements. The presence of foreign metal species is generally detrimental for the degradation of organic species in aqueous systems. Cr and V ion implanted TiO₂ have showed photocatalytic reactivity higher than TiO₂ for the decomposition of NO under solar beam irradiation.⁴ Choi *et al.*⁵ found that doping quantum-sized TiO₂ with Fe³⁺, Mo⁵⁺, Ru³⁺, Os³⁺, Re⁵⁺, V⁴⁺ and Rh³⁺ enhances the photoreactivity both for the oxidation of CHCl₃ and the reduction of CCl₄. The photocatalytic efficiency of TiO₂ toward the oxidation of 1,4-dichlorobenzene is improved by the introduction of WO₃ and MoO₃.^{6,7} and a beneficial influence of tungsten was found for the photodegradation of 4-nitrophenol.^{8,9} Also, in order to extend the absorption threshold of TiO₂ to visible light, the effects of some transition metal ion dopants such as Fe, V, Mn, Co and Ni have been investigated for the TiO₂ system.¹⁰

Carbon nanotubes (CNTs) attracted worldwide attention in the past decade because of their unique structural, mechanical and electronic conducting properties, corrosion resistance and stability and promising applications in transistors, field-emission tips, sensors, supercapacitors, catalyst supports and storage materials for hydrogen.¹¹⁻¹³ TiO₂/carbon nanotube (CNT) composites attracted more attention than others because of the excellent mechanical property, large surface area, and unique electrical and electronic properties of CNT.¹⁴ According to our previous works,¹⁵⁻¹⁷ we prepared the CNT/TiO₂ composites by a sol-gel method and obtained enhanced photocatalytic activity because CNT could be act as an electron sensitizer and donator to accept the photo-induced electron (e⁻) into the conduction band of TiO₂ particles under UV light irradiation.

In this paper, transition metal ion of Cr³⁺, Mg²⁺ and V³⁺ doped CNT/TiO₂ composites were synthesized by sol-gel method. The properties of prepared metal oxide-CNT/TiO₂ composites were characterized by BET surface area measurement, scanning electron microscopy (SEM), transmission electron microscopy (TEM), X-ray diffraction (XRD), and energy dispersive X-ray (EDX) analysis. Also, the photocatalytic properties of metal oxide-CNT/TiO₂ composites were simply checked by decomposing methylene blue (MB) solution under visible light irradiation. The absorbance of decomposed MB solution was determined by an UV/VIS spectrophotometer.

Experimental Procedure

Materials. Titanium *n*-butoxide (TNB, Ti{OC(CH₃)₃}₄, 99%) as titanium alkoxide precursor to form TiO₂ was purchased from Acros Organics (USA). Multi-walled carbon

nanotube (MWCNT, 95.9%) with diameter of ~ 20 nm and length of ~ 5 μm was purchased from Nanokanbon (Korea). MWCNT was used directly without any purification, but had to oxidize the surface to obtain more functional groups. *m*-chlorperbenzoic acid (MCPBA) was used as strong oxidants to oxidize the MWCNT which obtained from Acros Organics (USA). Chromium acetylacetonate ($\text{Cr}(\text{acac})_3$, $\text{Cr}(\text{C}_5\text{H}_8\text{O}_2)_3$, 97%) and vanadyl acetylacetonate ($\text{VO}(\text{acac})_2$, $\text{VO}(\text{C}_5\text{H}_8\text{O}_2)_2$, 98%) with magnesium acetate ($\text{Mg}(\text{CH}_3\text{COO})_2 \cdot 4\text{H}_2\text{O}$, 99%) were used as transition metal precursors which purchased from Sigma-Aldrich Chemistry (USA) and Dae-Jung Chemicals & Metals (Korea), respectively. Benzene (C_6H_6 , 99.5%), used as a solvent, was purchased from Samchun Pure Chemical (Korea). Methylene blue (MB, $\text{C}_{16}\text{H}_{18}\text{N}_3\text{S} \cdot \text{Cl} \cdot 3\text{H}_2\text{O}$) was used as analytical grade which purchased from Duksan Pure Chemical Co., Ltd, Korea. The pure TiO_2 and MWCNT/ TiO_2 photocatalysts were used as compare materials for photodegradation effect of MB solution. The pure TiO_2 , with anatase structure, is obtained from Duksan Pure Chemical (Korea). The MWCNT/ TiO_2 photocatalyst was prepared in our previous work.¹⁵

Preparation of Metal Oxide-CNT/ TiO_2 Composites. Due to the MWCNT is very stable, it needs to be treated with strong acids to introduce active function groups on their surface. We took 1.0 g MCPBA melted in 60 mL Benzene to prepare oxidizing agent. And then 0.2 g MWCNT was put into the oxidizing agent. The mixture was stirred with a magnet for 6 h at 343 K. Then the MWCNT was dried at 373 K and spared.

Three kinds of organometallic compounds $\text{Cr}(\text{acac})_3$, $\text{Mg}(\text{CH}_3\text{COO})_2$ and $\text{VO}(\text{acac})_2$ were used to prepare three kinds of metal oxides. $\text{Cr}(\text{acac})_3$ and $\text{VO}(\text{acac})_2$ were dissolved in benzene to prepare 0.01 M $\text{Cr}(\text{acac})_3$ and $\text{VO}(\text{acac})_2$ solution. $\text{Mg}(\text{CH}_3\text{COO})_2$ was dissolved in distilled water to prepare 0.01 M $\text{Mg}(\text{CH}_3\text{COO})_2$ solution. The same amount of oxidized MWCNT was put into same volume of these three kinds of solution. And then the solutions were homogenized at 343 K for 5 h using a shaking water bath with a shaking rate of 120 rpm/min. After reaction for 5 h, the solutions were transformed to the metal oxide-CNT gels, and these gels were heat treated at 873 K for 1 h with a heating rate of 279 K/min. Then metal oxide-CNT composites were prepared. In a separate preparation, TNB (4 mL) was dissolved in 46 mL of benzene with constant stirring to form

a TNB-benzene solution. Three kinds of prepared metal oxide-CNT composites were placed into this solution, respectively. The mixtures were then reacted at 343 K for 5 h using a shaking water bath at a shaking rate of 120 rpm/min. After this reaction, the mixtures were treated thermally at 873 K for 1 h at a heating rate of 279 K/min. Finally the metal oxide-CNT/ TiO_2 composites were obtained. The preparation condition and code of samples are listed in Table 1. And the schematics of MWCNT surface oxidation and deposition of organometallic compound on MWCNT was schematically illustrated in Figure 1.

Characterization. Synthesized metal oxide-CNT/ TiO_2 composites were characterized by various techniques. The BET surface area was measured using a Quantachrome surface area analyzer (Monosorb, USA). SEM (JSM-5600 JOEL, Japan) and TEM (JEM2000-FX, Japan) were used to observe the surface state and structure of metal oxide-CNT/ TiO_2 composites was carried out. XRD was used for crystal phase identification and estimation of the anatase-to-rutile ratio. XRD patterns were obtained at room temperature by using an X-ray generator (Shimata XD-D1, Japan) using $\text{CuK}\alpha$ radiation. EDX was used to measure the elemental analysis of metal oxide-CNT/ TiO_2 composites. The light absorption spectra of the samples were recorded with an UV/VIS spectrophotometer (Optizen POP, Mecasys Co., Ltd, Korea) in a range of 200–750 nm.

Photocatalytic Activity. The photocatalytic activity of metal oxide-CNT/ TiO_2 composites was taken out by decomposition of MB solution under irradiation of visible light. In an ordinary photocatalytic test performed at 25 $^\circ\text{C}$, 0.05 g photocatalyst was added to 50 mL of 1.0×10^{-5} mol/L MB solution and maintained in suspension by magnetic stirring. After stirring continuously in the dark for 2 h to ensure establishment of adsorption/desorption equilibrium

Table 1. Nomenclatures of metal oxide-CNT/ TiO_2 composites

Samples	Nomenclatures
MWCNT + 0.01 M $\text{Cr}(\text{acac})_3$ solution + TNB (4 mL)/benzene (46 mL)	MCT
MWCNT + 0.01 M $\text{Mg}(\text{CH}_3\text{COO})_2$ solution + TNB (4 mL)/benzene (46 mL)	MMT
MWCNT + 0.01 M $\text{VO}(\text{acac})_2$ solution + TNB (4 mL)/benzene (46 mL)	MVT

Figure 1. Schematics of deposition of organometallic compounds and TiO_2 on MWCNT.

of MB, the suspension was irradiated by visible light (8 W, $\lambda > 420$ nm, KLD-08L/P/N, Fawoo Technology) and it was treated as the starting point ($t=0$) of the reaction, where the concentration of MB was designated as c_0 . At specific time (30 min, 60 min, 90 min and 120 min) intervals a certain volume of the sample was withdrawn and centrifuged to remove the catalyst before analysis. The concentration of MB (c) solution during the photocatalytic degradation reaction was monitored through measuring the absorbance of the solution samples with UV/VIS spectrophotometer at $\lambda_{\max} = 660$ nm.^{18,19}

Results and Discussions

Characterization. Table 2 showed the BET surface area of pristine MWCNT, MCT, MMT and MVT. The BET surface area of pristine MWCNT was 299 m²/g. After treated by different organometallic compounds and TNB in benzene solvent, the BET surface area was decreased to 47 m²/g, 39.5 m²/g and 90 m²/g for samples MCT, MMT and MVT, respectively. It could be considered that the organometallic compounds and titanium oxide particles dispersed on the surface of MWCNT, which could clog the pore of MWCNT, thus decreased the surface area.

The micro-surface structures and morphology of metal oxide-CNT/TiO₂ composites prepared from different organometallic compounds were characterized by SEM and TEM. Figure 2 showed the SEM images of metal oxide-CNT/TiO₂ composites. For sample MCT, the Cr₂O₃ particles homogeneously mixed with MWCNT by TiO₂ particles uniformly distributed on their surface, as showed in Figure 2(a). For sample MMT, the porous structure could be observed in Figure 2(b), and the TiO₂ agglomerate was coated on the MgO-CNT composites. For sample MVT, it was difficult to distinguish the structure of metal, TiO₂ and CNT. So we used TEM to obtain the more detailed observations of prepared metal oxide-CNT/TiO₂ composites.

Figure 3 showed the TEM images of metal oxide-CNT/TiO₂ composites prepared from different organometallic compounds. For the sample MCT, the Cr₂O₃ and TiO₂ particles were homogeneously distributed on the surface of MWCNT. These structures would be shown the excellent photocatalytic activity. For sample MMT, the TiO₂ particles were distributed on the surface of MWCNT with some partial agglomerations. For sample MVT, TiO₂ particles with some agglomerates dispersed on the surface of MWCNT together with V₂O₃ particles. As we known, a good dispersion of small particles could provide more reactive sites for the reactants than aggregated particles. So it could be considered that the prepared samples MCT, MMT and MVT would have good photocatalytic activity for degradation of MB solution.

The XRD results for the metal oxide-CNT/TiO₂ composites prepared from different organometallic compounds were shown in Fig. 4. Sample MCT showed peaks at 24.5°, 33.6°, 36.2°, 41.4° and 50.5° 2 θ due to Cr₂O₃^{20,21} (JCPDS: 38-1479) and peaks at 25.3°, 37.8°, 48.0°, 53.8° and 54.9° 2 θ

Table 2. The BET surface area of pristine MWCNT, MCT, MMT and MVT

Samples	S _{BET} (m ² /g)
Pristine MWCNT	299
MCT	47
MMT	39.5
MVT	90

Figure 2. SEM images of metal oxide-CNT/TiO₂ composites prepared from different organometallic compounds; MCT (a), MMT (b) and MVT (c).

due to anatase TiO₂ (JCPDS: 21-1272). For sample MMT, apart from the (111) and (200) diffraction peaks of cubic MgO (JCPDS: 36-1377) structure from the substrate,^{22,23} all recognizable reflection peaks, at 25.3°, 37.8°, 48.0°, 53.8° and 54.9°, could be well indexed to the anatase TiO₂

Figure 3. TEM images of metal oxide-CNT/TiO₂ composites prepared from different organometallic compounds; MCT (a), MMT (b) and MVT (c).

structure. In sample MVT, the peaks at $2\theta = 36.2^\circ$, 41.2° due to V_2O_5 ^{24,25} (JCPDS: 34-0187) and peak at $2\theta = 27.4^\circ$ due to rutile structure of TiO₂ (JCPDS: 21-1276) and peaks at $2\theta = 48.0^\circ$ and 54.9° due to anatase structure of TiO₂. It could be indicated that after heat treatment at 873 K for 1 h, the organometallic compound precursors Cr(acac)₃, Mg(CH₃COO)₂, VO(acac)₂ and TNB have been changed to Cr₂O₃, MgO, V₂O₅ and TiO₂. The intensity of TiO₂ was decreased by an order of MMT, MCT and MVT, indicated the TiO₂ content in composites was also decreased by an order of MMT, MCT and MVT. It could be also observed that no reflection peaks from impurities existed in XRD patterns for all of samples, indicating the high purity of the products. On the other hand, the characteristic peaks of MWCNT could hardly be identified from the XRD patterns of all samples. It was thought that the absence of MWCNT aggregated pores was supported by the disappearance of CNTs characteristic peaks in XRD patterns.

EDX was conducted on several zones of metal oxide-

Figure 4. The XRD patterns of samples MCT, MMT and MVT.

Figure 5. EDX elemental microanalysis of metal oxide-CNT/TiO₂ composites prepared from different organometallic compounds; MCT (a), MMT (b) and MVT (c).

CNT/TiO₂ composites prepared from different organometallic compounds. The main elements found in a representative analysis were shown in Figure 5. Three kinds of main elements C, O and Ti were existed in all of samples and metal element Cr, Mg and V were existed in samples MCT, MMT and MVT, respectively, and without any other impure elements. However, the Ti content in sample MMT was much more than that in samples MCT and MVT. This result was agreed with the results of XRD which the intensity of TiO₂ was strongest in sample MMT among these three kinds of samples.

Figure 6. MB removal by photocatalytic degradation for pure TiO₂, CNT/TiO₂ composites, MCT, MMT and MVT under irradiation of visible light for 120 min.

Photocatalytic Activity. Figure 6 showed MB removal by photocatalytic degradation for pure TiO₂, CNT/TiO₂ composites, MCT, MMT and MVT under irradiation of visible light for 120 min. As mentioned above, the TiO₂ could only show photocatalytic activity under UV light, due to its wide band gap (3.2 eV for anatase), and did not act with the solar light effectively. So in the present study, pure TiO₂ shows a little of photocatalytic activity only decreased 3.4% of MB solution under visible light after 120 min. For CNT/TiO₂ composite, after irradiation for 120 min under visible light, the concentration of MB solution was decreased 15%, more than pristine TiO₂. For metal oxide-CNT/TiO₂ composites, they showed much more photocatalytic activity than CNT/TiO₂ composite. And the concentration of MB solution was decreased 48%, 32% and 46% for samples MCT, MMT and MVT, respectively. In addition, the kinetic plots were shown by apparent first-order linear transform $-\ln(c/c_0)$ against time function $f(t)$ in Figure 7. Table 3 showed the apparent kinetic constant (k_{app}) of pure TiO₂, CNT/TiO₂ composites MCT, MMT and MVT. The k_{app} of the pure TiO₂ and CNT/TiO₂ composites was $4.38 \times 10^{-4} \text{ min}^{-1}$ and $9.94 \times 10^{-4} \text{ min}^{-1}$. However, the k_{app} of metal oxide-CNT/TiO₂ composites was much higher than that of pure pure TiO₂ and CNT/TiO₂ composites, which were $3.92 \times 10^{-3} \text{ min}^{-1}$, $3.22 \times 10^{-3} \text{ min}^{-1}$ and $3.73 \times 10^{-3} \text{ min}^{-1}$ for samples MCT, MMT and MVT, respectively. The introduction of MWCNT and metal oxide into matrix obviously created kinetic combination effect in MB degradation with an increase in the rate constant by the combination factor of 8.9, 7.35 and 8.5 for samples MCT, MMT and MVT, respectively. It could be indicated that the metal oxide-CNT/TiO₂ composites had more photocatalytic activities under irradiation of visible light region.

The photocatalytic activity of TiO₂ could be controlled by the following factors: (i) light absorption wavelength; (ii) rate of the electron or hole induced redox reaction; and (iii) recombination of the electron-hole. The mechanism of photodegradation of dye solution for metal oxide-CNT/TiO₂ composites was shown in Figure 8. When a transition metal

Figure 7. Apparent first-order linear transform $-\ln(c/c_0)$ against $f(t)$ of MB degradation kinetic plots for pure TiO₂, CNT/TiO₂ composites, MCT, MMT and MVT.

Table 3. The apparent kinetic constant (k_{app}) and combination factor (R) of pure TiO₂, CNT/TiO₂ composites, MCT, MMT and MVT

Samples	$k_{app} (\text{min}^{-1})$	R
Pure TiO ₂	4.38×10^{-4}	1
CNT/TiO ₂	9.94×10^{-4}	2.26
MCT	3.92×10^{-3}	8.9
MMT	3.22×10^{-3}	7.35
MVT	3.73×10^{-3}	8.5

ion (Cr^{3+} , Mg^{2+} or V^{3+}) was incorporated into the TiO₂ lattice, the dopant level appears between the valence band and conduction band of TiO₂,^{21,26,27} thereby altering the band-gap energy and shifting the absorbance edge to the visible light region. According to previous studies, MWCNT could act as an electron sensitizer and donor in the composite photocatalyst to accept a photo-induced electron (e^-) into the conduction band of TiO₂ particles under light irradiation, thereby increased the number of electrons as well as the rate of electron-induced redox reactions. The

Figure 8. A convenient mechanism for the metal oxide-CNT/TiO₂ composites.

addition of a transition metal also had a charge trapping effect. Charge trapping can be demonstrated by the following equations:⁵

The holes could transfer to the TiO₂ surface and react with OH⁻ to produce active OH•. When a transition metal ion replaced Ti ions in the TiO₂ lattice, most of the dopant levels appeared between the valence band and conduction band of TiO₂. This could increase the surface trapping rate of the carrier and retard the electron-hole recombination^{23,28} as well as enhance the photocatalytic activity of TiO₂. Finally, the MB solution is decomposed to CO₂, H₂O, NO₃⁻, NH₄⁺ and SO₄²⁻.

Conclusions

We introduced transition metals into CNT/TiO₂ composites to prepare metal oxide-CNT/TiO₂ composites by using three kinds of organometallic compounds (Cr(acac)₃, Mg(CH₃COO)₂ and VO(acac)₂). The BET surface area was decreased a lot after treatment by organometallic compounds and titanium for all of metal oxide-CNT/TiO₂ composites. For the sample MCT, the Cr₂O₃ and TiO₂ particles were homogeneously distributed on the surface of MWCNT. For sample MMT, the TiO₂ particles were distributed on the surface of MWCNT with some partial agglomerations. For sample MVT, TiO₂ particles with some agglomerates dispersed on the surface of MWCNT together with V₂O₃ particles. From the XRD results, Cr₂O₃, MgO and V₂O₃ structures were existed in samples MCT, MMT and MVT, respectively. The anatase type TiO₂ structures were also existed in samples MCT and MMT, and a mixture structures of anatase and rutile type TiO₂ were existed in sample MVT. Three kinds of main elements (C, O and Ti) were existed in all of metal oxide-CNT/TiO₂ composites, and element Cr, Mg and V was existed in samples MCT, MMT and MVT, respectively. Comparison with pure TiO₂ and CNT/TiO₂ composites, the prepared metal oxide-CNT/TiO₂ composites showed very high photocatalytic degradation efficiency for MB solution under visible light irradiation. Because the transition metal ions could incorporate into the lattice of TiO₂, alter the band-gap energy and shift the absorbance edge of TiO₂ to the visible light region.

References

- Hoffmann, M. R.; Martin, S. T.; Choi, W.; Bahnemann, D. W. *Chem. Rev.* **1995**, 95, 69-96.
- Lee, D. H.; Choi, S. Y. *Met. Mater. Inter.* **2004**, 10, 357-360.
- Snn, F. Y.; Wu, M.; Li, W. G. *Chin. J. Catal.* **1998**, 19, 229-233.
- Anpo, M.; Ichihashi, Y.; Takeuchi, M.; Yamashita, H. In *Science and Technology in Catalysis 1998*; Delmon, B., Yates, J. T., Eds.; Kodansha: Tokyo, 1999; p 305.
- Choi, W.; Termin, A.; Hoffmann, M. R. *J. Phys. Chem.* **1994**, 98, 13669-13679.
- Do, Y. R.; Lee, W.; Dwight, K.; Wold, A. *J. Solid State Chem.* **1994**, 108, 198-201.
- Papp, J.; Soled, S.; Dwight, K.; Wold, A. *Chem. Mater.* **1994**, 6, 496-500.
- Marci, G.; Palmisano, L.; Sclafani, A.; Venezia, A. M.; Campostrini, R.; Carturan, G.; Martin, C.; Rives, V.; Solana, G. *J. Chem. Soc.* **1996**, 92, 819-829.
- Martin, C.; Solana, G.; Rives, V.; Marci, G.; Palmisano, L.; Sclafani, A. *Catal. Lett.* **1997**, 49, 235-243.
- Jiang, H.; Gao, L. *Mater. Chem. Phys.* **2002**, 77, 878-881.
- Bachtold, A.; Hadley, P.; Nakanishi, T.; Dekker, C. *Science* **2001**, 294, 1317-1320.
- An, K. H.; Kim, W. S.; Park, Y. S.; Choi, Y. C.; Lee, S. M.; Chung, D. C.; Bae, D. J.; Lim, S. C.; Lee, Y. H. *Adv. Mater.* **2001**, 13, 497-500.
- Tang, H.; Chen, J. H.; Huang, Z. P.; Wang, D. Z.; Ren, Z. F.; Nie, L. H. *Carbon* **2004**, 42, 191-197.
- Eder, D.; Windle, A. H. *J. Mater. Chem.* **2008**, 18, 2036-2043.
- Chen, M. L.; Zhang, F. J.; Oh, W. C. *Journal of the Korean Ceramic Society* **2008**, 45, 651-657.
- Oh, W. C.; Zhang, F. J.; Chen, M. L. *Bull. Korean Chem. Soc.* **2009**, 30, 2637-2642.
- Chen, M. L.; Zhang, F. J.; Oh, W. C. *New Carbon Materials* **2009**, 24, 159-166.
- Chen, M. L.; Bae, J. S.; Oh, W. C. *Bull. Korean Chem. Soc.* **2006**, 27, 1423-1328.
- Chen, M. L.; Lim, C. S.; Oh, W. C. *J. Cera. Proc. Res.* **2007**, 8, 119-124.
- Miyazaki, H.; Matsui, H.; Nagano, T.; Karuppachamy, S.; Ito, S.; Yoshihara, M. *Appl. Surf. Sci.* **2008**, 254, 7365-7369.
- Chen, M. L.; Cho, K. Y.; Oh, W. C. *J. Mater. Sci.* DOI 10.1007/s10853-010-4751-6.
- Kim, H. W.; Shim, S. H.; Lee, J. W.; Lee, C. M. *J. Korean Phys. Soc.* **2007**, 51, 204-208.
- Chen, M. L.; Zhang, F. J.; Oh, W. C. *Korean J. Mater. Res.* **2010**, 20, 345-350.
- Matsui, H.; Okajima, T.; Karuppachamy, S.; Yoshihara, M. *J. Alloy. Compound.* **2009**, 468, L27-L32.
- Oh, W. C.; Zhang, F. J.; Chen, M. L. *J. Ind. Eng. Chem.* **2010**, 16, 299-304.
- Dong, Y. L.; Won, J. L.; Jae, S. S.; Jung, H. K.; Yang, S. K. *Comput. Mater. Sci.* **2004**, 30, 383-388.
- Chen, M. L.; Zhang, F. J.; Zhang, K.; Meng, Z. D.; Oh, W. C. *J. Chem. Res.* **2010**, 5, 283-287.
- Colmenares, J. C.; Aramendia, M. A.; Marinas, A.; Marinas, J. M.; Urbano, F. J. *Catal. A Gen.* **2006**, 306, 120-127.