PEDOT:PSS/Single Wall Carbon Nanotube Composite Nanoparticles as an Additive for Electric-double Layer Capacitor

Jong Hyeok Park^{a,†}, Sang Young Lee^{b,†}, Jong Hun Kim^c, and Sunho Ahn^c

^a Department of Chemical Engineering, Sungkyunkwan University, Suwon 440-746, Republic of Korea

^b Department of Chemical Engineering, Kangwon National University, Chuncheon, Kangwondo 200-701, Republic of Korea

^c Research Park, LG Chem, Ltd., 104-1, Moonji-dong, Yuseong-gu, Daejeon 305-380, Republic of Korea

ABSTRACT :

The unique effects of highly conductive conducting polymer/SWNT (single walled carbon nanotube) composite nanoparticles in electric double layer capacitors are studied for the enhancement of the adhesive properties, specific capacitance and power characteristics of the electrode. Because the conducting polymer/SWNT composite material, which is believed to act as a polymer binder, an active material for charge storage and a conducting agent, is well distributed on the activated carbon, greatly enhanced adhesion properties, cell capacitance and power characteristics were obtained.

Keywords :

Received September 13, 2012 : Accepted September 30, 2012

1. Introduction

Supercapacitors have attracted much attention due to their high power capability and long-term cycling properties.¹⁻⁹⁾ They are generally classified into two categories, depending on the charge-storage mechanism. In electric double layer capacitors (EDLCs), the performance is correlated with the specific surface area of the activated carbons (AC), but is also influenced by other parameters, such as the pore size.^{10,11)} Capacitors in the other class, called pseudocapacitors, are based on materials with pseudocapacitance characteristics, such as conducting polymers¹²⁻¹⁴⁾ or other metal oxide based inorganic materials.¹⁵⁻¹⁷⁾ Among them, ACs are the most widely used electrode material for supercapacitors because of their high surface area.¹⁸⁾

Generally, the electrodes for EDLCs are composed of AC as the active material, a polymeric binder, and a

conducting agent to reduce the series resistance. Generally, ACs show relatively low conductivity, thus leading to a severe loss of power density in EDLCs since the power density (P) is given by the following equation;¹⁸⁾

$$P = V^2 / (4ESR \times M) \quad (1)$$

where ESR is the equivalent series resistance and M is the total mass of the two electrodes.

The first approach to increase the power density of EDLCs is the addition of a minor electrode component, such as carbon nanotubes, to improve the electrical conductivity.¹⁹⁾ However, owing to their low energy storage characteristics, the replacement of ACs by highly electrically conducting materials reduces the energy density of the EDLCs. The second possible method of increasing the power density and energy density of EDLCs is to use as little polymeric binder as possible. As the content of the polymeric binder is decreased, the power density and energy density of the EDLC increase, owing to the decrease in the series

[†]Corresponding author. Tel.:

E-mail address: lutts@skku.edu, syleek@kangwon.ac.kr

resistance and the increase in the content of AC leading to the formation of more electric double layers, respectively. However, decreasing the polymeric binder content also has certain drawbacks, such as the decrease of the adhesive force between the AC and current collector.

In order to solve the above-mentioned problems, our strategy is to use a conducting polymer/SWNT composite material localized on the surface of AC exhibiting high conductivity and adhesive properties, which can act simultaneously as a conducting agent and binder material. Moreover, conducting polymers can contribute charge storage by acting as a redox-active material, because they can be readily converted between the oxidized (p-doped) and reduced (n-doped) states by switching the applied potential.²⁰⁻²² In this work, we report on the fabrication and characterization of an EDLC with a new additive which is composed of PEDOT:PSS (poly(3,4-ethylenedioxythiophene):poly(styrene sulfonate)) and SWNTs.

2. Experimental

The PEDOT:PSS and SWNTs were obtained from H. C. Starck and Iljin nanotech, respectively. After the purification of the SWNTs by a previously reported procedure,²³ a concentrated PEDOT:PSS/SWNT solution was prepared (40 wt% SWNT). Then, PEDOT:PSS/SWNT composite powders were prepared by the freeze drying method.

The homogeneous pastes used for the EDLC electrodes were prepared by the addition of AC (MSC-20, Kancei Coke, Japan), a polymeric binder (PTFE, Aldrich Chem), conducting agent (super-p) and conducting polymer powders (PEDOT:PSS/SWNT or PEDOT:PSS) to water. The pastes were spread on an

Al current collector and the thickness of the electrode (~50 mm) was controlled by the rolling process. The morphology of the electrode was investigated with a high resolution scanning electron microscope (Philips SEM 535 M). A homogeneous mixture of the powders was pelletized to produce a pellet of the correct size and then its resistance was checked by the four-point probe method using a Hioki tester. The peel test was carried out with a stress-strain tester (Instron).

Sandwich-type cells containing the prepared electrodes were built using a coin-cell type structure, with a PE separator between the positive and negative electrodes. For the charge-discharge tests, 2032 coin-type cells with an electrode area of 1.4 cm² were used. The electrolyte consisted of 1 M LiPF₆ dissolved in ethylene-methylcarbonate (EC-EMC; 3:7 v/v). In an argon filled glove box, the coin cells were assembled and filled with the electrolyte. The charge-discharge cycling tests of the cells were performed using a TOSCAT-3000U system (Toyo System Co., Ltd.). The cells were charged up to 2.5 V at a current density of 1 mA/cm² then discharged to 0 V with various discharge current densities. Cyclic voltammetry was performed using an EG&G 273A potentiostat (scan rate: 5 mV/cm²). The specific cell capacitance (*C*) was measured by the charge-discharge test and calculated using the equation, $I \times Dt/DV$, where *I* is the current density, *t* the discharge time and *V* is the voltage. The specific capacitance of each electrode was calculated by means of the equation, $2C/M$, where *M* is the total weight of the AC.

3. Results and Discussion

The scanning electron micrographs (SEM) of the SWNTs before and after the purification process are

Fig. 1. SEM images of SWNTs before (a) and after (b) their purification. (c) PEDNT composite powder.

Fig. 2. SEM images of AC based electrodes: (a) AC: Super-p:PTFE, 90:5:5 by wt., (b) AC:Super-p:PTFE: PEDNT, 85:5:5 by wt.

shown in Figs. 1(a) and (b), respectively. The PEDOT:PSS/SWNT composite powders (hereafter PEDNT) prepared by the lyophilization method are shown in Fig. 1 (c). The SEM images of the electrodes made with AC:Super-p:PTFE (90:5:5 by wt.) and AC:Super-p:PTFE:PEDNT (85:5:5 by wt.) are also shown in Figs. 2(a) and (b), respectively. The size of the AC particles is about 5~10 μm . The surface of the AC particles in the latter has well dispersed PEDNT nanoparticles compared with that of the AC without the PEDNT nanoparticle, thus improving the adhesion properties between the AC particles themselves or the AC particles and current collector. In addition, the PEDNT nanoparticles can reduce the interfacial electrical resistance among the AC particles, owing to their high conductivity. This is very important to obtain a high power density from the supercapacitors. To confirm the role of PEDNT as an adhesion enhancer, two kinds of electrodes were prepared and their adhesion properties characterized by measuring the adhesion force between the electrode layer and the

Fig. 3. Adhesion force of AC based electrodes: (square) AC:Super-p:PTFE, 90:5:10 by wt., (circle) AC:Super-p:PEDNT, 85:5:10 by wt.

Table 1. Electric resistance of conductive materials

Materials	Resistivity (Ω/sq)
Super-p	50
PEDOT:PSS	250
PEDNT	15
SWNT	10

current collector. As shown in Fig. 3, the electrode with PEDNT (AC:Super-p: PEDNT, 85:5:10 by wt.) showed a ~2 times higher adhesion force compared with that of the electrode with PTFE (AC:Super-p:PTFE, 85:5:10 by wt.). To confirm the role of PEDNT as an conductivity enhancer, the resistivity of the super-p and PEDNT were characterized by the four-point probe method. As can be seen in Table 1, PEDNT showed a lower resistivity compared with that of super-p (widely used conducting agent for EDLCs).

The cyclic voltammograms (CVs) in 1 M LiPF_6 solution of the AC based electrode with PEDNT (AC:Super-p:PTFE:PEDNT, 85:5:5 by wt.) are shown in Fig. 4. The shape of the CV curve is rectangular, which means that the electrode is suitable for supercapacitor applications. The CV of the electrode did not indicate the presence of any oxidation or reduction peak currents from the PEDOT:PSS, because of its capacitive-like charge storage behavior.²⁴⁾

To demonstrate the practical application of these electrodes with the new additive, a capacitor was fabricated and its charge-discharge properties were evaluated. A unit cell was constructed using the same

Fig. 4. CVs of the electrode (AC:Super-p:PTFE:PEDNT, 85:5:5:5 by wt.); the scan rate is 10 mV/s.

electrodes for both the positive and negative electrodes. The charge-discharge curves of the EDLC using the electrode with the additive (AC:Super-p:PTFE:PEDNT, 85:5:5:5 by wt.) are presented in Fig. 4. The EDLCs were tested at different constant current densities in the range of 1 mA/cm² to 20 mA/cm² between 0 V and 2.5 V. During the charging process, Li⁺ and PF₆⁻ ions are physically adsorbed onto the interface of the AC, while the opposite behavior occurs during the discharging process. In Fig. 5, the voltage of the EDLC varies almost linearly with time during both the charging and discharging processes.

Three kinds of AC-based EDLCs were prepared and their specific capacitances were compared as a function of the current density in the range between 1 mA/cm² and 20 mA/cm². The electrodes consisting of AC:PEDNT(85:15 by wt.), AC:Super-p:PEDNT:

Fig. 5. Charge-discharge curves for unit cell capacitor at a current density of 2 mA/cm².

Fig. 6. Specific capacitance as a function of the current density; AC:Super-p:PTFE, 85:10:5 by wt. (○), AC:Super-p:PTFE:PEDNT, 85:5:5:5 by wt. (□), AC:PEDNT, 85:15 by wt.(△).

PTFE (85:5:5:5 by wt.) and AC:Super-p:PTFE (85:10:5 by wt.) as a reference were used as EDLCs. From Fig. 6, it can be seen that the specific capacitance of the EDLC with only 15 wt% PEDNT was the worst. Because PEDNT is a PEDOT-PSS based conducting polymer, it has strongly hydrophilic characteristics. Hence, the wettability of the electrode with only 15 wt% PEDNT with organic electrolytes was very poor. This might be the reason why the EDLC with 15 wt% PEDNT showed the worst behavior. However, the EDLC with 5 wt% PEDNT, 5 wt% conducting agent (Super-p) and 5 wt% binder showed enhanced power characteristics compared to those of the EDLC with the reference cell (AC:Super-p:PTFE (85:10:5 by wt)). This means that PEDNT acts as powerful conductive agent in the EDLC. From Fig. 6, it can also be seen that the specific capacitance of AC:Super-p:PEDNT:PTFE (85:5:5:5 by wt.) was enhanced to a certain degree by adding 5 wt% PEDNT. This means that the PEDNT present among the AC particles not only contributes to the reduction of the cell resistance, but also to the enhancement of the energy storage properties.

These unique effects of the PEDNT in the EDLC were compared with those of PEDOT/PSS (Baytron P) by replacing PEDNT with PEDOT/PSS. A new electrode with this composition (AC:Super-p:PTFE:PEDOT/PSS, 85:5:5:5 by wt.) was thus prepared. Fig. 7 shows the specific capacitance as a function of the current density in the range between 1 mA/cm² and 20 mA/cm². As can be seen from Fig. 7, when

Fig. 7. Specific capacitance normalized with total mass of electrode as a function of current density. AC:Super-p:PTFE:PEDNT, 85:5:5:5 by wt. (□) and AC:Super-p:PTFE:PEDOT/PSS, 85:5:5:5 by wt. (■).

the PEDNT was replaced by PEDOT/PSS, the initial cell capacitance and power properties were dramatically decreased, compared with those of the EDLC with PEDNT. From the comparison of the cell capacitances at a low current density, we can conclude that the energy storage ability of the AC is much improved by adding PEDNT to the electrode. In addition, when PEDOT/PSS was added to the electrode instead of PEDNT, the decrease in the specific capacitance at a high discharge current density was significant, demonstrating the inferior power characteristics of this electrode.

Fig. 8 shows the capacitance behavior of the EDLC prepared with the electrode made of AC:Super-

Fig. 8. Normalized variation in capacitance as a function of cycle number (AC:Super-p:PTFE: PEDNT, 85:5:5:5 by wt. vs. AC:Super-p:PTFE, 85:10:5 by wt. (○)).

p:PTFE:PEDNT (85:5:5:5 by wt.) during the cyclability test. The EDLC was tested at a constant charge/discharge current density (10 mA/cm^2) between 0 V and 2.5 V. As shown in Fig. 8, the EDLC showed nearly the same capacitance as its initial value after 1000 cycles, even though the pseudocapacitive material was added. This means that the positive properties of PEDNT are not degraded as the cycle number is increased.

4. Conclusions

We investigated the positive effects of PEDNT on AC-based EDLCs. The experimental results showed that due to the effects of the unique conducting polymer, the EDLCs exhibited superior performance in terms of both their discharge specific capacitance and power characteristics compared with those of the AC based EDLC and PEDOT/PSS based EDLC. PEDNT plays an important role in improving the electronic conductivity by acting as a conducting agent and the cell capacitance by acting as an active material. The higher electronic conductivity of PEDNT might improve the AC utilization for charge storage. Moreover, the electrode with PEDNT showed better adhesion to the metal current collector. We believe that PEDNT can be a powerful additive for increasing the specific capacitance, power characteristics, and adhesive properties.

References

1. M. A. T. Gilmarin and J. P. Hart, *Analyst*, **120**, 1029 (1995).
2. Y. Matsumra, S. Wang and J. Mondori, *Carbon*, **33**, 1457 (1995).
3. J. H. Park, J. M. Ko and O. O. Park, *J. Power Sources*, **105**, 20 (2002).
4. J. H. Park and O. O. Park, *J. Power Sources*, **109**, 121 (2002).
5. J. H. Park, J. M. Ko and O. O. Park, *J. Electrochem. Soc.*, **150**, A864 (2003).
6. J. H. Park, O. O. Park, K. H. Shin, C. S. Chin and J. H. Kim, *Electrochem. Solid-State Lett.*, **5**, H7 (2002).
7. V. Khomenko, E. Raymundo-Pinero, E. Frackowiak and F. Beguin, *App. Phys A*, **82**, 567 (2006).
8. E. Frackowiak, G. Lota, J. Machnikowski, C. and Vix-Guterl, F. Beguin, *Electrochim. Acta*, **51**, 2209 (2006).
9. F. Beguin, K. Szostak, G. Lota and E. Frackowiak, *Adv. Mater.*, **17**, 2380 (2005).
10. D. Qu and H. Shi, *J. Power Sources*, **74**, 99 (1998).
11. O. Barbieri, M. Hahn, A. Herzog and R. Kotz, *Carbon*,

- 43**, 1765 (2005).
12. A. Laforgue, P. Simson, C. Sarrazin and J. F. Fauvarque, *J. Power Sources*, **80**, 142 (1999).
 13. K. Jurewicz, S. Delpeux, V. Bertagna, F. Beguin and E. Frackowiak, *Chem. Phys. Lett.* **347**, 36 (2001).
 14. E. Frackowiak, V. Khomenko, K. Jurewicz, K. Lota and F. Beguin, *J. Power Sources* **153**, 413 (2006).
 15. N. L. Wu, *Mater. Chem. Phys.* **75**, 6 (2002).
 16. Y. U. Jeong and A. Manthiram, *J. Electrochem. Soc.* **149**, A1419 (2002).
 17. E. Raymundo-Pinero, V. Khomenko, E. Frackowiak and F. Beguin, *J. Electrochem. Soc.* **152**, A229 (2005).
 18. E. Raymundo-Pinero, F. Leroux and F. Beguin, *Adv. Mater.* **18**, 1877 (2006).
 19. J. Sandler, M. S. P. Shaffer, T. Prasse, W. Bauhofer, K. Schulte and A. H. Windle, *Polymer*, **40**, 5967 (1999).
 20. R. Liu, I. Cho and S. B. Lee, *Nanotechnology*, **19**, 215710 (2008).
 21. R. Liu and S. B. Lee, *J. Am. Chem. Soc.*, **130**, 2942 (2008).
 22. S. Patra and N. Munichandraiah, *J. Appl. Polym. Sci.*, **106**, 1160 (2007).
 23. A. C. Dillon, T. Gennett, K. M. Jones, J. L. Alleman, P. A. Parilla and M. J. Heben, *Adv. Mater.* **11**, 1354 (1999).
 24. C. Arbizzani, M. Mastragostino and M. Rossi, *Electrochem. Commun.*, **4**, 545 (2002).