Physical and Microwave Dielectric Properties of the MgO-SiO₂ System

Deuk Ho Yeon, Chan Su Han, Sung Hoon Key, Hyo Eun Kim, Jong Yun Kang* and Yong Soo Cho[†]

Department of Materials Science and Engineering, Yonsei University, Seoul 120-749, Korea

*Thin Film Materials Research Center, Korea Institute of Science and Technology, Seoul 130-650, Korea

(Received September 12, 2009 : Received in revised form October 6, 2009 : Accepted October 12, 2009)

Abstract Unreported dielectrics based on the binary system of MgO-SiO₂ were investigated as potential candidates for microwave dielectric applications, particularly those demanding a high fired density and high quality factors. Extensive dielectric compositions having different molar ratios of MgO to SiO₂, such as 2:1, 3:1, 4:1, and 5:1, were prepared by conventional solid state reactions between MgO and SiO₂. 1 mol% of V₂O₅ was added to aid sintering for improved densification. The dielectric compositions were found to consist of two distinguishable phases of Mg₂SiO₄ and MgO beyond the 2:1 compositional ratio, which determined the final physical and dielectric properties of the corresponding composite samples. The increase of the ratio of MgO to SiO₂ tended to improve fired density and quality factor (Q) without increasing grain size. As a promising composition, the 5MgO.SiO₂ sample sintered at 1400 °C exhibited a low dielectric constant of 7.9 and a high Q × f (frequency) value of ~99,600 at 13.7 GHz.

Key words Mg₂SiO₄, MgO-SiO₂, dielectric, microwave frequency, quality factor.

1. Introduction

Recent developments of millimeter-wave frequency applications such as dielectric resonators, ceramic substrates, waveguides, and antennas have demanded nonconventional dielectric materials that are designed to exhibit unusual dielectric performance.¹⁾ Dielectric materials with extremely high quality factor (Q) and low dielectric constant (k) have been the major concern since those dielectric properties are the primary factors in achieving high selectivity, lowering power dissipation, and reducing the delay time of electronic signal transmission.²⁻⁵⁾ A number of millimeter-wave dielectrics including Mg₂SiO₄, Zn₂SiO₄, MgTiO₃, MgAl₂O₄ and glass-based compounds have been recently reported as promising candidates.⁴⁻¹¹⁾

Among those candidates, forsterite (2MgO.SiO₂, Mg₂SiO₄) that has not only the high quality factor but also low dielectric constant seems to be one of the ideal millimeter-wave dielectric materials. There have been several reports on Mg₂SiO₄, basically with intention to improve dielectric properties through compositional modification and novel powder processing.^{7,8,12-16)} For instance, the combination of Mg₂SiO₄ with Zn₂SiO₄ was found to be an effective way to increase physical and thus dielectric pro-

perties at relatively lower sintering temperatures.¹⁴⁾ Sano et al.¹⁶⁾ reported that the use of nano-sized precursors in preparing dense Mg₂SiO₄ could enhance transparency and dielectric loss (tan δ) up to the level of 10⁻⁴.

This work deals with extended combinations of MgO and SiO₂ beyond the 2:1 molar ratio in order to investigate potential improvement of microwave dielectric properties. Four different MgO:SiO₂ molar ratios of 2:1, 3:1, 4:1 and 5:1 are studied in terms of physical and dielectric properties. These compositional combinations have not been considered as a dielectric candidate for high frequency applications until now.

2. Experimental Procedure

Bulk samples based on the MgO-SiO₂ system were prepared by conventional solid state reactions between MgO and SiO₂. Raw materials of reagent MgO (98%, Aldrich Co.) and SiO₂ (99.6%, Aldrich Co.) were mixed by ball-milling in ethanol for 24 hrs to prepare four different compositions of 2MgO.SiO₂, 3MgO.SiO₂, 4MgO.SiO₂ and 5MgO.SiO₂. 1 mol% V₂O₅ (99.99%, Aldrich Co.) was added as a sintering aid through the initial mixing. The mixtures were dried at 120 °C in an oven and calcined at 1200 °C for 3h in ambient atmosphere. The calcined powder was sieved and pressed uniaxially at ~80 MPa after mixing with an 1.5 wt.% polyvinyl alcohol (PVA) solution as a binder.

[†]Corresponding author
E-Mail : ycho@yonsei.ac.kr (Y. S. Cho)

Each pellet was sintered at a temperature of 1300 °C and 1400 °C for 4 h with a fixed heating rate of 5 °C/min.

The crystalline phases were determined using an x-ray diffractometer (XRD; Rigaku B/Max-2500/PC, Tokyo, Japan) with CuK α radiation. Microstructures of the sintered samples were examined by scanning electron microscopy (SEM; Model S-4200, Hitachi, Nissei Sangyo, Japan). Bulk density was determined by using the Archimedes principle. Microwave dielectric properties of the sintered samples were measured using a network analyzer (Agilent 8720ES, Palo Alto, CA). Dielectric characteristics, such as dielectric constant k and quality factor Q , were determined by the Hakki-Coleman dielectric resonator method in the S₂₁ transmission mode.¹⁷⁾

3. Result and discussion

Figs. 1 and 2 show XRD patterns of the 2MgO·SiO₂, 3MgO·SiO₂, 4MgO·SiO₂ and 5MgO·SiO₂ samples sintered at 1300 °C and 1400 °C for 4 h, respectively. As expected, the 2MgO·SiO₂ composition showed phase-pure Mg₂SiO₄ (forsterite) at both temperatures. All other samples showed the mixture of Mg₂SiO₄ and residual MgO phases regardless of sintering temperature. It indicates that further increase in the content of MgO relative to SiO₂ beyond 2:1

Fig. 1. XRD patterns of the (a) 2MgO·SiO₂, (b) 3MgO·SiO₂, (c) 4MgO·SiO₂ and (d) 5MgO·SiO₂ samples sintered at 1300 °C for 4 h.

Fig. 2. XRD patterns of the (a) 2MgO·SiO₂, (b) 3MgO·SiO₂, (c) 4MgO·SiO₂ and (d) 5MgO·SiO₂ samples sintered at 1400 °C for 4 h.

does not create any unexpected phase except for the Mg₂SiO₄ and residual MgO. The relative peak intensity of MgO phase was found to increase proportionally with increasing the content of MgO in the MgO-SiO₂ system at both temperatures. The relative content of the Mg₂SiO₄ phase was roughly calculated by comparing the strongest peak intensity of each phase using the following simple equation,

$$\text{forsterite phase \%} = \frac{I_{\text{Mg}_2\text{SiO}_4}}{I_{\text{Mg}_2\text{SiO}_4} + I_{\text{MgO}}} \times 100 \quad (1)$$

where $I_{\text{Mg}_2\text{SiO}_4}$ and I_{MgO} are the strongest intensity peaks of the Mg₂SiO₄ and MgO phases, respectively. These % contents of each phase estimated for all compositions at both temperatures are summarized in Table 1. These calculated values are actually invariant at both temperatures and are reasonable when each reaction sequence is considered. For example, the relative content of Mg₂SiO₄ phase was obtained as ~33% in 4MgO·SiO₂ at both temperatures and the value must be expected from the reaction sequence of $4\text{MgO} + \text{SiO}_2 = \text{Mg}_2\text{SiO}_4 + 2\text{MgO}$. Note that the molar ratio of Mg₂SiO₄ to MgO after the reaction is 1:2. Accordingly, the phase development of the MgO-SiO₂ system essentially leads to the composite between Mg₂SiO₄ and MgO and the relative content of each phase in the composite can be easily assumed from the simple

Table 1. Estimated phase contents and physical properties of the MgO-SiO₂ samples sintered at 1300 and 1400 °C for 4 h.

MgO : SiO ₂ (mol %)	Sintering Temp. (°C)	Estimated phase content (%)		Relative density (%)	x-y shrinkage (%)	Grain size (μm)
		Mg ₂ SiO ₄	MgO			
2:1	1300	100	0	91.1	15.1	2.7
3:1	1300	50.6	49.4	93.7	16.6	1.5
4:1	1300	33.1	66.9	93.5	16.8	1.3
5:1	1300	24.5	75.5	93.8	17.0	1.2
2:1	1400	100	0	93.1	15.5	5.1
3:1	1400	51.6	48.4	95.2	17.9	2.6
4:1	1400	32.8	67.2	95.7	18.1	2.1
5:1	1400	24.5	75.5	96.3	18.3	1.6

Fig. 3. Surface microstructures of the (a) 2MgO:SiO₂, (b) 3MgO:SiO₂, (c) 4MgO:SiO₂ and (d) 5MgO:SiO₂ samples sintered at 1300 °C for 4 h.

reaction between MgO and SiO₂.

Table 1 also shows the physical properties, i.e., relative fired density and linear shrinkage, of the samples sintered at 1300 and 1400 °C for 4 h. The relative density was expressed in percentage relative to the theoretical value calculated from the composite composition consisting of the two Mg₂SiO₄ and MgO phases. It is clear that the density value tends to be improved by adding the excessive Mg contents compared to that of 2MgO:SiO₂ composition. This increasing tendency became more apparent at 1400 °C where the 5MgO:SiO₂ composition reached a maximum density of 96.3%. The shrinkage values also followed the

similar trends with density, but there was no significant change among the 3MgO:SiO₂, 4MgO:SiO₂ and 5MgO:SiO₂ samples.

Fig. 3 shows surface microstructures of the samples sintered at 1300 °C for 4 h. Microstructural characteristics depended on each composition. All samples show the promising surface microstructural characteristics, which can be featured with denser grain structures with low porosity. The 2MgO:SiO₂ composition seemed to be less densified compared to the other compositions. The trend of surface densification depending on the composition is well supported by the measured density and linear shrinkage values

Fig. 4. Surface microstructures of the (a) 2MgO/SiO₂, (b) 3MgO/SiO₂, (c) 4MgO/SiO₂ and (d) 5MgO/SiO₂ samples sintered at 1400 °C for 4 h.

in Table 1.

Fig. 4 shows the surface microstructures of the MgO-SiO₂ samples sintered at the higher temperature of 1400 °C for 4 h. The microstructural development with increasing sintering temperature can be explained as typical sintering behavior that can be characterized by the temperature-dependant transition from small grains to large ones with accompanying reduction of porosity. Calculated grains sizes for the samples sintered at both temperatures are represented in Table 1. There was a distinct trend of reducing grain size with increasing the relative content of MgO in the material system at both temperatures. This result may be reasonable because MgO itself is very refractive and hard to be densified in this temperature range of 1300 to 1400 °C.^{18,19)} It is likely that MgO acts as a grain growth inhibitor and lead to small grain sizes depending on the content of residual MgO. However, it is still interesting to note that the use of excessive MgO does not create low density or low shrinkage even the overall grain size tends to become smaller. For example, the 5MgO/SiO₂ sample showed the smallest grain size of 1.6 μm while having the highest relative density of 96.3% at 1400 °C.

Fig. 5 shows the variation of microwave dielectric properties, i.e., dielectric constant and $Q \times f$ (frequency), for the MgO-SiO₂ samples at both temperatures. Overall

Fig. 5. Dielectric constant and $Q \times f$ values as a function of MgO/SiO₂ ratio for the samples sintered at 1300 and 1400 °C for 4 h.

dielectric properties of the samples seemed to be promising at the high resonant frequencies > 10 GHz, which can be highlighted specifically with high $Q \times f$ values

greater than 60,000. Specifically, the dielectric properties of the MgO-SiO₂ system must be understood as determined by respective contributions of Mg₂SiO₄ and residual MgO as well as the degree of densification. Dielectric constant of the samples apparently increased with increasing the ratio of MgO to SiO₂. It was difficult to correlate the observed dielectric properties of the composite system in conjunction with the mixing rule of two phases, forsterite and MgO, since the dielectric constant of highly-anisotropic MgO is unknown at GHz. The dielectric constant ~6.6 of the 2:1 composition, i.e., stoichiometric forsterite, is comparable to the reported dielectric constant.⁷⁾ Similarly, the $Q \times f$ values also tended to be enhanced with increasing the ratio of MgO to SiO₂. This is an unexpected desirable result, which must be useful in designing microwave devices a higher quality factor. There was no significant difference in dielectric properties between 1300 and 1400 °C except for the 5MgO·SiO₂ sample. As the most promising result, the 5MgO·SiO₂ sample sintered at 1400 °C exhibited a low dielectric constant of 7.9 and a high $Q \times f$ value of ~99,600 at 13.7 GHz. The TCF value measured was ranged of -30 to -56 ppm/K without a distinct dependence of compositional ratio between forsterite and MgO.

4. Conclusions

New composite-typed dielectric materials based on the MgO-SiO₂ system were investigated over the extensive compositional range from 2:1 to 5:1. As expected, 2MgO·SiO₂ composition showed pure Mg₂SiO₄ phase but all other phases consisted of Mg₂SiO₄ and unreacted MgO phases. The reaction sequence of $x\text{MgO} + \text{SiO}_2 = \text{Mg}_2\text{SiO}_4 + (x - 2)\text{MgO}$ was confirmed by the simple estimation of the relative content of each phase on the basis of XRD patterns obtained at both sintering temperatures of 1300 and 1400 °C. Even though the residual MgO does not react with Mg₂SiO₄, it was found that densification can be improved even in the 5MgO·SiO₂ sample by reducing porosity effectively while keeping grain size smaller. As an example of enhanced dielectric properties compared to

the 2MgO·SiO₂ (Mg₂SiO₄) composition, 5MgO·SiO₂ demonstrated a dielectric constant of 7.9 and a $Q \times f$ value of ~99,600 at 13.7 GHz after sintering at 1400 °C for 4 h.

Acknowledgement

This work was supported by a grant of the Ministry of Knowledge Economy, Korea, specified by the Foundation R&D Program for Core Technology of Materials.

References

1. S. J. Kim and E. S. Kim, *Kor. J. Mater. Res.*, **17**, 442 (2007).
2. R. J. Cava, *J. Mater. Chem.*, **11**, 54 (2001).
3. I. M. Reaney and D. Iddles, *J. Am. Ceram. Soc.*, **89**, 2063 (2006).
4. H. Ohsato, *J. Ceram. Soc. Jpn.*, **113**, 703 (2005).
5. K. X. Song and X. M. Chen, *Mater. Lett.*, **62**, 520 (2008).
6. G. W. Brindley and R. Hayami, *Philos. Mag.*, **12**, 505 (1965).
7. T. Sugiyama, T. Tsunooka, K. Kakimoto and H. Ohsato, *J. Eur. Ceram. Soc.*, **26**, 2097 (2006).
8. K. X. Song, X. M. Chen and X. C. Fan, *J. Am. Ceram. Soc.*, **90**, 1808 (2007).
9. K. P. Surendram, P. V. Bijumon, P. Mohanan and M. T. Sebastian, *Appl. Phys. A.*, **81**, 823 (2005).
10. V. M. Ferreira, F. Azough, J. L. Baptista and R. Freer, *Ferroelectrics*, **133**, 127 (1992).
11. J. Sugihara, K. Kakimoto, I. Kagomiya and H. Ohsato, *J. Eur. Ceram. Soc.*, **27**, 3105 (2007).
12. K. X. Song, X. M. Chen and C. W. Zheng, *Ceram. Int.*, **34**, 917 (2008).
13. H. Ohsato, T. Tsunooka, M. Ando, Y. Ohishi, Y. Miyauchi and K. Kakimoto, *J. Kor. Ceram. Soc.*, **40**, 350 (2003).
14. S. T. Lee, Y. H. Jo, H. E. Kim, D. H. Youn, I. J. Choi, S. H. Key, C. Y. Kang, W. S. Hong and Y. S. Cho, *Adv. Appl. Ceram.* (DOI: 10.1179, in press).
15. A. Saberi, B. Alinejad, Z. Negahdari, F. Kazemi and A. Almasi, *Mater. Res. Bull.*, **42**, 666 (2007).
16. S. Sano, N. Saito, S. Matsuda, N. Ohashi, H. Haneda, Y. Arita and M. Takemoto, *J. Am. Ceram. Soc.*, **89**, 568 (2006).
17. B. W. Hakki and P. D. Coleman, *IRE Trans. Microwave Theory Tech.*, **MTT-8**, 402 (1960).
18. A. V. Gropyanov and V. M. Gropyanov, *Refract. Ind. Ceram.*, **42**, 162 (2001).
19. S. M. Zubakov, P. N. Babin and A. K. Akishev, *Refract. Ind. Ceram.*, **20**, 311 (1979).