Effects of Chamber Pressure on Dielectric Properties of Sputtered MgTiO₃ Films for Multilayer Ceramic Capacitors

Sang-Shik Park[†]

School of Nano & Materials Engineering, Kyungpook National University, Kyungpook 742-711, Korea

(Received June 29, 2010 : Received in revised form July 10, 2010 : Accepted July 19, 2010)

Abstract MgTiO₃ thin films were prepared by r.f. magnetron sputtering in order to prepare miniaturized NPO type MLCCs. MgTiO₃ films showed a polycrystalline structure of ilmenite characterized by the appearance of (110) and (202) peaks. The intensity of the peaks decreased with an increase in the chamber pressure due to the decrease of crystallinity which resulted from the decrease of kinetic energy of the sputtered atoms. The films annealed at 600°C for 60min. showed a fine grained microstructure without micro-cracks. The grain size and roughness of the MgTiO₃ films decreased with the increase of chamber pressure. The average surface roughness was 1.425~0.313 nm for MgTiO₃ films prepared at 10~70 mTorr. MgTiO₃ films showed a dielectric constant of 17~19.7 and a dissipation factor of 2.1~4.9% at 1MHz. The dielectric constant of the films is similar to that of bulk ceramics. The dielectric constant and the dissipation factor decreased with the increase of the chamber pressure due to the decrease of grain size and crystallinity. The leakage current density was 10⁻⁵~10⁻⁷ A/cm² at 200kV/cm and this value decreased with the increase of the chamber pressure. The small grain size and smooth surface microstructure of the films deposited at high chamber pressure resulted in a low leakage current density. MgTiO₃ films showed a near zero temperature coefficient and satisfied the specifications for NPO type materials. The dielectric properties of the MgTiO₃ thin films prepared by sputtering suggest the feasibility of their application for MLCCs.

Key words MgTiO₃ films, MLCC, capacitance, leakage current.

1. Introduction

Magnesium titanate based materials are extensively used as a dielectric of NPO type multilayer ceramic capacitors (MLCCs), which have been widely used in electric and electronic devices. It is known that MgTiO₃ bulk ceramics exhibit a low dielectric loss, a near zero temperature coefficient and dielectric constant of the range of 17~20 in microwave frequencies.^{1,2)} The recent developments in MLCC fabrication technology have focused on the improvement of volumetric efficiency, cost reduction, improvement in reliability, and the design of new products with improved performance.³⁻⁵⁾ Especially, with the recent tendency in miniaturization of electronic equipments, MLCCs are required to have a high electrostatic capacitance and also to be miniaturized. For enhancing of the electrostatic capacitance of MLCCs, one of the most effective means is to provide a thin dielectric layer between the inner electrodes. The capacitance of the MLCC is expressed by the following equation.

$$C = N (\epsilon_0 \cdot \epsilon_r \cdot A) / d \quad (1)$$

Where, C is capacitance, N layer number, ϵ_0 permittivity

in vacuum, ϵ_r dielectric constant of ceramic film, A the surface area of electrode, and d thickness of dielectrics.

Therefore, in the capacitor of equivalent size, the increase of capacitance can be obtained by increase of ϵ_r and N and decrease of d.

The dielectric sheets of MLCCs have been formed by die coater and lip coater and thickness of dielectric sheets has been decreased to about 1 μ m levels.⁶⁾ However, because the preparation of thinner dielectric layers by casting method such as die coater and lip coater is very difficult, it is needed to consider new method except casting method. The development of thin film capacitors designed by thin film technologies have been required for next generation capacitors.^{7,8)} Vapor deposition processes have inherent advantages over traditional MLCC technology, such as the ability to deposit very thin, uniform and defect free dielectric sheets. Our recent works showed that MLCCs could be manufactured by thin film technology. Fig. 1 shows a SEM cross-section image of MLCC prepared by e-beam evaporation using a shadow mask. Alternating dielectric and electrode layers can be prepared through the x and z-axis movement of shadow mask.⁹⁾

Although MgTiO₃ films have been studied for application in microwave devices, the studies for MLCCs is very uncommon. In this work, MgTiO₃ films were deposited using R.F. magnetron sputtering technique. The

[†]Corresponding author
E-Mail : parkss@knu.ac.kr (S. -S. Park)

Fig. 1. SEM cross-section image of multilayer capacitor with BaTiO_3 and Al alternating layers.⁹⁾

Table 1. Preparation conditions of MgTiO_3 thin films.

Parameters	Conditions
Target-substrate distance	60 mm
Substrate	p-Si(100), Pt/TiO ₂ /Si
Ar:O ₂	1:1
R.f. power	200 W
Base pressure	5×10^{-6} Torr
Working pressure	10–70 mTorr
Substrate temperature	Room temp.

aim of this study is to evaluate the effects of deposition pressure on dielectric properties of MgTiO_3 films. Also, the relationships between microstructure and dielectric properties of films were investigated.

2. Experimental Procedure

MgTiO_3 thin films were deposited on p-Si(100) substrate using a conventional r.f. magnetron sputtering system. MgTiO_3 ceramic target was prepared by conventional sintering methods from high purity (> 99.9%) MgO and TiO₂ powders. After working chamber was pumped down to 1×10^{-6} Torr, sputtering gas mixture (Ar:O₂ = 1:1) was injected and then, MgTiO_3 films were deposited at various pressure of 10 mTorr to 70 mTorr. The target was pre-sputtered for 10 min. to eliminate contamination of target and maintain homogeneity of target composition. The detailed deposition conditions were described in Table 1. The crystal structure of the films was determined by X-ray diffraction (XRD, Panalytical X'pert pro) employing Cu α radiation and Ni filter. The microstructure and composition of MgTiO_3 films were determined using scanning electron microscopy and energy dispersive x-ray spectroscopy (SEM-EDX, Jeol JSM-6700F) and The roughness of each film was measured with atomic force microscopy (AFM, Park system XE-100). For the electrical measurement, platinum top electrode with 100 nm thickness and 100 μm

Fig. 2. XRD patterns of MgTiO_3 films as a function of chamber pressure.

diameter were deposited using dc sputtering, that is, metal-insulator-metal (MIM) capacitors with a Pt/ MgTiO_3 /Pt/TiO₂/Si structure were fabricated. The dielectric constant and dissipation factor as a function of frequency were measured using an impedance-gain phase analyzer (Hewlett-Packard 4194A). The current-voltage (I-V) measurements were performed with a picoammeter (Hewlett-Packard 4140B) under conditions of a 0.1V voltage step and a delay time of 0.1s.

3. Results and Discussion

Fig. 2 shows XRD patterns of the MgTiO_3 films annealed at 600°C after deposited using r.f. power of 200W. XRD patterns indicated that MgTiO_3 films showed a polycrystalline structure of the ilmenite characterized by the appearance of (110) and (202) peaks. The intensity of peaks decreased with increasing the chamber pressure and the (110) and (202) peaks disappeared at 50 and 70 mTorr. In general, the sputtered atoms show the reduction of surface mobility on substrate surface with the increase of chamber pressure. Therefore, the decrease of peak intensity is probably due to decrease of crystallinity which resulted from decrease of kinetic energy of the sputtered atoms.

Fig. 3 shows SEM surface images of MgTiO_3 films deposited on Si(100) substrate as a function of chamber pressure. The films were annealed at 600°C for 60min. The surface microstructures revealed that MgTiO_3 films had a fine grained microstructure without micro-cracks. The SEM images indicated that grain size decreased with increasing the chamber pressure. The decrease of grain size with chamber pressure is due to that high chamber pressure decreases mean free path of sputtered particles, resulting in a decrease of the kinetic energy of arriving atoms.¹⁰⁾ Accordingly, it is inferred that the small grain size at high chamber pressure is attributed to atoms with

Fig. 3. SEM surface morphologies of MgTiO_3 films; (a) 10mTorr, (b) 30mTorr, (c) 50mTorr and (d) 70mTorr.

low kinetic energy.

Fig. 4 shows deposition rate for MgTiO_3 thin films of Fig. 2. The deposition rate of films was remarkably decreased with increasing a chamber pressure. The deposition rate of films revealed 3.05, 2.14, 0.625 and 0.373 nm/min at chamber pressure of 10, 30, 50 and 70 mTorr, respectively. The calculated mean free path at 10 mTorr was 7.2 times of that at 70 mTorr. Because deposition rate is directly related to mean free path, the decrease of deposition rate is due to the increase of scattering from the gas atoms.

It is important to investigate the surface morphology of

Fig. 4. Variation of deposition rate of MgTiO_3 films prepared under various chamber pressures.

MgTiO_3 films, since the surface morphology will affect the electrical properties of films. The influences of chamber pressure on the morphologies of MgTiO_3 films were examined by AFM. Fig. 5 shows three dimensional AFM images of MgTiO_3 films. The average roughness of films decreased with increasing the chamber pressure. The average surface roughness was 1.425, 1.408, 0.689 and 0.313 nm for MgTiO_3 films prepared at 10, 30, 50, 70 mTorr, respectively. Because of atomic shadowing effects, the surface roughness can increase with film thickness. However, the similar roughness tendency was shown in films with similar thickness prepared by controlling the deposition time. These results imply that in the case of low deposition rate at a high pressure, newly arrived atoms have more sufficient time to relax to low energy configurations, leading to the formation of smoother films.¹¹⁾

Fig. 6 shows the variation of dielectric constant and dissipation factor ($\tan\delta$) as a function of frequency for MgTiO_3 films deposited at various chamber pressures. The dielectric constant and dissipation factor of MgTiO_3 films exhibited little dispersion at the high frequencies up to 5MHz. The dielectric constant at a frequency range of 100kHz to 10MHz decreased with increasing the chamber pressure. The decrease of dielectric constant with chamber pressure is attributed to the decrease in grain size of the MgTiO_3 films. The dielectric constant of films deposited at various chamber pressures were 19.7 to 17 at 1MHz. The dielectric constant of the films is similar to that of

bulk ceramics.^{12,13)} The dissipation factor of MgTiO₃ films decreased with increasing the chamber pressure except that of 30mTorr. The dissipation factor of films deposited at various chamber pressures were 4.9 to 2.1% at 1MHz. The dissipation factor of the films is higher than that of films prepared by metal-organic solution deposition.¹⁴⁾ It is reported that a structural disorder can be caused by surface morphology and/or the lattice disruption at the surface or the interface between film and electrode.¹⁵⁾ Since the films did not show the dispersion due to the space charges, the increase of dissipation factor at low chamber pressure is related to surface morphology. The structural disorder of MgTiO₃ films prepared by r.f. magnetron sputtering may affects the large dissipation factor.

The leakage current in MLCCs should be as low as

possible to have better insulation resistance. Fig. 7(a) shows the leakage current characteristics of MgTiO₃ films deposited on Pt/TiO₂/Si substrate. In the measurement of current-voltage, the applied voltage was swept from -5V to 5V. As shown in Fig., leakage current density decrease gradually with increasing chamber pressure. Generally, the leakage current is influenced by the crystallinity, the grain size and the surface roughness. It may be inferred that small grain size and smooth surface microstructure at high chamber pressure result in low leakage current density. The leakage current density of the films was about $8 \times 10^{-6} \sim 2 \times 10^{-7} \text{ A/cm}^2$ at 200kV/cm. Fig. 7(b) shows capacitance vs. temperature property of MgTiO₃ films. For the NPO type dielectrics, the capacitance must not change by more than $\pm 30\text{ppm}/^\circ\text{C}$ from the value at 25°C over the tem-

Fig. 5. AFM surface morphologies of MgTiO₃ films; (a) 10mTorr, (b) 30mTorr, (c) 50mTorr and (d) 70mTorr.

Fig. 6. (a) Dielectric constant and (b) dissipation factor of MgTiO₃ films as a function of frequency.

Fig. 7. (a) Leakage current and (b) capacitance change with temperature of MgTiO₃ films.

perature range -55 to 125°C . MgTiO₃ films show a near zero temperature coefficient. The capacitance change with operating temperature satisfied the specification for NPO type materials.

4. Conclusion

The application of MgTiO₃ thin films for NPO type MLCCs was proposed in this study. MgTiO₃ thin films were prepared by r.f. magnetron sputtering. Particularly, the relationships between chamber pressure and dielectric properties of films were investigated. The grain size and roughness of MgTiO₃ films decreased with an increase of chamber pressure due to short mean free path and low deposition rate. The grain size and roughness of films influences dielectric constant, dissipation factor and leakage current. The dielectric constant and dissipation factor of MgTiO₃ films obtained by sputtering are $17\sim 19.7$ and $4.9\sim 2.1\%$ at 1MHz, respectively and are comparable to that by other deposition methods. Leakage current density is about $8 \times 10^{-6} \sim 2 \times 10^{-7} \text{ A/cm}^2$ at 200 kV/cm . These results suggest the feasibility that the miniaturized NPO type MLCCs can be prepared by R.F. magnetron sputtering.

Acknowledgement

This work was supported by the Kyungpook National University Research Grant, 2008.

References

1. Y. Jiang, R. Guo and A. S. Bhalla, *J. Phys. Chem. Solids*, **59**, 611 (1998).
2. M. P. Baura-Pena, M. J. Martinez-Lope and M. E. Garcia-Clarel, *J. Mater. Sci.*, **26**, 4341 (1991).
3. T. Nomura, N. Kawano, J. Yamamatsu and T. Arashi, *Jpn. J. Appl. Phys.*, **34**, 5389 (1995).
4. Y. Okino, H. Sizuno, S. Kusumi and H. Kisi, *Jpn. J. Appl. Phys.*, **33**, 5393 (1994).
5. J. Yamamatsu, N. Kawano, T. Arashi, A. Sato, Y. Nakano and T. Nomura, *J. Power Sources*, **60**, 199 (1996).
6. Y. Sakabe, Y. Takeshima and K. Tanaka, *J. Electroceram.*, **3**, 115 (1999).
7. R. Xu, M. Shen, S. Ge, Z. Gan and W. Cao, *Thin Solid Films*, **406**, 113 (2002).
8. Y. Takeshima, T. Tanaka and Y. Sakabe, *J. Am. Ceram. Soc.*, **106**, 441 (2000).
9. S. Park, *Integrated Ferroelectrics*, **74**, 87 (2005).
10. L. T. Lamont and A. Lange, *J. Vac. Sci. Technol.*, **7**, 198 (1970).
11. Y. Zhao, Y. Qian, W. Yu and Z. Chen, *Thin Solid Films*, **286**, 45 (2002).
12. J. Bernard, D. Hpuivet, J. El Fallah and J. M. Haussonne, *J. Eur. Ceram. Soc.*, **24**, 1877 (2004).
13. K. Wakino, *Ferroelectrics*, **91**, 69 (1989).
14. Y. H. Choi and J. Lee, *Thin Solid Films*, **385**, 43 (2001).
15. V. M. Ferreira, J. L. Baptista, S. Kamba and J. Petzelt, *J. Mater. Sci.*, **28**, 5894 (1993).