Fabrication and Characterization of BCP Nano Particle Loaded PCL Fiber and Their Biocompatibility

Thi-Phuong Nguyen and Byong-Taek Lee[†]

Department of Biomedical Engineering and Materials, School of Medicine, Soonchunhyang University 366-1, Ssangyong-dong, Cheonan, Chungnam 330-090, Korea

(Received June 21, 2010 : Received in revised form July 27, 2010 : Accepted July 27, 2010)

Abstract The electrospinning process was established as a promising method to fabricate nano and micro-textured scaffolds for tissue engineering applications. A BCP-loaded PCL micro-textured scaffold thus can be a viable option. The biocompatibility as well as the mechanical properties of such scaffold materials should be optimized for this purpose. In this study, a composite scaffold of poly (ϵ -caprolactone) (PCL)-biphase calcium phosphate (BCP) was successfully fabricated by electrospinning. EDS and XRD data show successful loading of BCP nano particles in the PCL fibers. Morphological characterization of fibers shows that with a higher loaded BCP content the fiber surface was rougher and the diameter was approximately 1 to 7 μ m. Tensile modulus and ultimate tensile stress reached their highest values in the PCL- 10 wt% BCP composite. When content of nano ceramic particles was low, they were dispersed in the fibers as reinforcements for the polymer matrix. However, at a high content of ceramic particles, the particles tend to agglomerate and lead to decreasing tensile modulus and ultimate stress of the PCL-BCP composite mats. Therefore, the use of nano BCP content for distribution in fiber polymer using BCP for reinforcement is limited. Tensile strain decreased with increasing content of BCP loading. From in vitro study using MG-63 osteoblast cells and L-929 fibroblast like cells, it was confirmed that electrospun PCL-BCP composite mats were biocompatible and that spreading behavior was good. As BCP content increased, the area of cell spreading on the surface of the mats also increased. Cells showed the best adherence on the surface of composite mats at 50 wt% BCP for both L-929 fibroblast-like cells and MG-63 osteoblast cell. PCL- BCP composites are a promising material for application in bone scaffolds.

Key words electrospinning, composite, polycaprolactone, biphase calcium phosphate, MG-63 osteoblast cell.

1. Introduction

Due to non-toxic biocompatibility and biodegradation, polymers like PLLA, PLGA, and PCL have been used in fabrication of 3D fiber structures with high surface area and interconnected pores by the electrospinning process for applications in biomedical fields, such as drug delivery and scaffold for tissue engineering.¹⁻³⁾ Among them, electrospinning poly (ϵ -caprolactone) (PCL) in particular has been investigated for bone scaffolds due to slow degradation rate. Its structural stability provides an excellent environment for promotion of cell growth for transfer of degradable scaffold.³⁻⁷⁾ However, using of electrospun PCL is still restricted because of its poor mechanical properties and high hydrophobicity.³⁰⁾ In order to achieve better strength, as well as biocompatibility, cell proliferation and rate of degradation of composite scaffold have always been regarded as important for selection of reinforced bio-ceramics particles. For improvement of both bioactivity and mechanical properties of the polymer, the inorganic

reinforcing phase such as nano HAp has been incorporated into the polymeric.⁸⁻¹⁰⁾ Electrospun composite scaffolds composed of PCL and nano HAp that can improve mechanical properties and cell proliferation using murine embryonic stem cells and human mesenchymal stem cells have been reported.¹¹⁻¹⁴⁾

Calcium phosphate ceramic is known for its biocompatibility, bioactivity, and osteoconductivity. In addition, calcium phosphate had a high adsorption capacity for serum proteins, such as fibronectin and vitronectin.¹⁵⁾ Thus, using of calcium phosphate could result in enhanced attachment of osteoblast cells. On the other hand, calcium phosphate gradually dissolved to release calcium and phosphate ions, which are beneficial to bone formation.¹⁶⁾ Among calcium phosphate ceramics, such as hydroxyapatite (HAp) and β -TCP (β -tricalcium phosphate), osteoinductivity of BCP (HAp and TCP) has been reported as more efficient than HAp alone for repair of periodontal defects, and having better osteoinduction than single phasic HAp or β -TCP. However, their range of biodegradation rate still cannot satisfy the requirement for biodegradable biomaterials. Therefore, the combination of HAp, α -TCP, and β -TCP may present a scope for optimal biodegradable

[†]Corresponding author
E-Mail : lbt@sch.ac.kr (B. -T. Lee)

calcium phosphates. On the other hand, α -TCP hydrolyses through a dissolution precipitation, giving rise to the formation of an network of calcium deficient hydroxyapatite crystals. It is well known that calcium deficient hydroxyapatite shows more similar features to biological apatite with respect to conventional stoichiometric hydroxyapatite. The high reactivity with water makes the α -TCP very interesting as reinforcement. The combination of HAp, α -TCP, and β -TCP can improve the mechanical properties, induce the proper biodegradation and promote the osteointegration that is increasing the bioactivity of the composite.

The release behavior of BCP materials can be modified by impregnation of BCP particles in a bio-degradable polymer matrix. By adding the BCP particles in PCL polymer we can achieve this. Recently, the electrospinning process was established as a promising method to fabricate nano and micro-textured scaffold for tissue engineering application.¹⁷⁾ The BCP-loaded PCL micro-textured scaffold thus can be a viable option. The bio-compatibility as well as the mechanical properties of the scaffold materials should be optimized for this purpose.

In this study, we fabricated PCL-BCP composites by electrospinning with the aim of improving mechanical properties and cell adhesion of the scaffold. To confirm that muscle cell and bone cell can attach well on and biocompatible of electrospun fibrous PCL-BCP using L-929 fibroblast-like cells and MG-63 osteoblast cells in vitro study. Indirect cytotoxicity and cell attachment were investigated. The effects of BCP contents on tensile strength and cell adhesion behaviors were investigated. PCL-BCP composites are promising material for bone scaffold application such as bone sheet which contact with bone and muscle.

2. Experimental Procedure

2.1 Material

Polycaprolactone pellets (PCL, Mn 80,000, Sigma-Aldrich, USA) and acetone (SK Chemicals Co, Korea) were used as starting materials for fabrication of fibrous PCL-BCP composite mats. BCP powder was synthesized using a microwave assisted process with a particle size of around 90-100 nm.¹⁸⁾

For in vitro study, hexamethyldisilazane (HDMS, Sigma-Aldrich, USA), dimethylsulfoxide 99.0% (DMSO, Samchun Pure Chemical Co, LTD, Korea), ethanol (Merck, Germany), fetal bovine serum (FBS), penicillin streptomycin antibiotic (PS), 3-[4,5-dimethylthiazol-2-yl]-2,5 diphenyltetrazolium bromide (MTT) solution, trypsin-EDTA (Gibco, Carlsbad, CA), phosphate buffered saline tablets (PBS) (Amresco, Korea), glutaraldehyde 25% (Showa, Chemicals Co, Korea), RPMI (RPMI-1640) and Dulbecco's Modification of Eagle's MEM (DMEM) (HyClone, Logan, UT) were used. While

L-929 fibroblast like cells were derived from mouse fibroblasts, MG-63 osteoblast cells were derived from human osteosarcomas. Both types of cells were obtained from the KCB (Korean Cell Bank).

2.2 Fabrication of fibrous PCL-BCP composite mats

For fabrication of fibrous PCL-BCP composite mats, nano powder BCP (HAp: TCP, 1:1) with different weight ratio percentages (0, 10, 30, and 50 wt.%) of PCL was blended in acetone, with a PCL concentration of 12 wt.%. The mixture was sonicated for 2 hours at 50°C to dissolve PCL, and then stirred for 4 hours to produce a homo-geneous slurry.

The slurry was poured into a plastic syringe equipped with a 21 G needle, fixed in a digitally controlled syringe pump (KD Scientific), and electrospun as follows: voltage 20 kV (NNC-30KV-2mA portable type, NanoNC, Korea), needle-target distance 12 cm, feed rate 2 ml h⁻¹. The composition of the electrospun composites was reported as mixed condition and was used for the final composites too.

2.3 Characterization

The morphology of the fibrous PCL-BCP composite was examined using a scanning electron microscope (SEM) and EDS techniques. X-ray diffraction (XRD) and differential scanning calorimetry (DSC) were used in characterization of electrospun fiber mats.

XRD (D/MAX-250, Rigaku, Japan, $\lambda = 1.541$ nm, 40 kV) was used for crystal analysis. XRD analysis at a scanning speed of 2° min⁻¹.

For characterization of electrospun fibrous PCL-BCP composite mats, differential scanning calorimetry (DSC) (Mettler Toledo, DSC822E, Korea) measurements were conducted using TA instruments. The samples were heated from -50°C to 150°C at a rate of 10°C min⁻¹. The melting point (T_m) was obtained from the DSC thermogram. The degree of crystallinity of PCL was calculated according to:

$$X_c = \Delta H_m / \Delta H_0 \quad (1)$$

Where X_c is crystallinity degree, ΔH_m is melting enthalpy, which is derived from the DSC curves, ΔH_0 is the theoretical enthalpy of the fully crystalline PCL, which has a value of 136 J g⁻¹.¹⁴⁾

2.4 Tensile testing

Uniaxial tensile tests were carried out on rectangular specimens measuring 3.0 mm in width and 20.0 mm in length ($n = 4$). Mechanical tests were performed at 1 mm min⁻¹ for rupture by an electromechanical machine equipped with a 0.5 kg load cell (ASTM, D882, Korea). Measurement of tensile strength was carried out using a universal testing machine (Unitech TM, R&B, Korea). Tensile modulus (E), ultimate stress (σ_{max}), and ultimate percent deformation (ϵ_f) were calculated for the crosssectional area of

the tensile specimen.

2.5 Cytotoxicity assay

Cytotoxicity of each electrospun PCL-BCP composite mat was determined using the MTT assay. Determination of cellular viability % against fibrous PCL-BCP composite mats followed the standard testing protocol.¹⁹⁾ In brief, for sterilization purposes, the sample mats were immersible in 70% ethanol for 30 minutes. The samples were washed with PBS to eliminate ethanol. RPMI medium was used as the diluent for obtaining the sample extract. The specimens were maintained in a shaking incubator at 100 rpm and 37°C for 3 days. Following incubation, the extracts were collected by filtration, and were serially diluted (100, 75, 50, 25%). The diluted extracts were then placed in a 96-well culture plate that had been previously sub-cultured with L-929 fibroblast like cells (1×10^4 cell/well). The 96-well culture plate was then placed in a CO₂ incubator and incubated at 37°C for 3 days. After incubation, the MTT solution (20 μ l of 5 mg/ml) was added to the wells, and the plate was incubated at 37°C for 4 hours. Finally, the solution in the culture plates was removed from the plate, and 200 μ l of DMSO was added to each well, and kept for 1 hour for formation of purple fomazan crystals. Absorbance of the solution was determined at a wavelength of 595 nm by ELISA reader (EL, 312, Biokinetics reader, Bio-Tek instruments). Samples were tested in quadruplicate.

2.6 Cell adhesion

Cell adhesion is one of the most important aspects of cellular interaction with other materials.¹⁹⁾ For determination of cell adhesion capacity, one cell morphology was used. L-929 fibroblast like cells and MG-63 osteoblast cells were used in observation of the attachment behavior of the cells onto electrospun fibrous PCL-BCP composite mats. First, the samples were sterilized with 70% ethanol, and then washed with PBS to eliminate ethanol. Freshly subcultured cells were then counted and 1×10^6 cells were dropped by micropipette onto each of the samples in 24-well culture plates. The 24-well culture plate was placed in a CO₂ incubator and incubated for 30, 60, and 90 minutes. Following the incubation period, these cells were fixed onto the surfaces by maintenance of the cell-sample in 2% glutaraldehyde for 15 minutes, followed by washing with PBS. Samples were dehydrated using serial ethanol dehydration of 50, 75, 90, 95, and 100%. Reagent graded HMDS was used to dry the samples. Finally, the morphology of the attached cells on the samples was observed by SEM (model JMS-5410 LV JEOL).

3. Results and Discussion

3.1 Characterization of microstructure and material properties of fibrous PCL-BCP composite mats

Fig. 1 shows SEM micrographs of PCL-BCP composite

Fig. 1. SEM micrographs of fibrous PCL-BCP composite mats, depending on BCP content at: (a) 0 wt%, (b) 10 wt%, (c) 30 wt% and (d) 50 wt%.

mats, depending on BCP contents, respectively. These SEM micrographs show a highly interconnected pores with high surface area of electrospun PCL-BCP composite mats. Their microstructures were observed with a combined micro-texture, with fine and coarse fibres in the mats and without dependence on BCP contents. Fiber diameter was approximately 1 to 7 μm . Results of BCP powder content loading in PCL fibers clearly showed that at 0 and 10 wt.% the fibers had a smooth surface, as shown in Fig. 1(a, b). However, as BCP increased up to 30 wt.%, the surface of the fiber became rough due to the appearance of BCP powder on the surface of the fiber, as shown by the arrows in Fig. 1(c). And at the highest BCP content of 50 wt.%, fibers showed the roughest surface, as shown in Fig. 1(d). These results are comparable with those from Wutticharoenmong's report.¹²⁾ Furthermore, from EDS (Fig.

Fig. 2. SEM micrograph and EDS profile of a fibrous PCL-50 wt.% BCP composite.

Fig. 3. XRD profiles of fibrous PCL-BCP composite mats (a) PCL-0 wt.% BCP, (b) BCP nano powder, (c) PCL-30 wt.% BCP and (d) PCL-50 wt.% BCP.

2) taken from the region marked P in Fig. 1(d), it was confirmed that the fibers existed with C, O, Ca, and P due to the composing elements of PCL and BCP powder.

Fig. 3 shows the XRD profiles of fibrous PCL-BCP composite mats (a) PCL-0 wt.% BCP, (b) BCP nano powder, (c) PCL-30 wt.% BCP, and (d) PCL-50 wt.% BCP, respectively. XRD profiles of a fibrous PCL mat with 2 peaks are seen in Fig. 3(a). XRD profiles of raw BCP powders are seen in Fig. 3(b,e). Fig. 3(c) shows XRD profile of a PCL-30 wt.% BCP composite mat with 2 peaks PCL and lower intensity of HAp, β -TCP peaks without any α -TCP peaks. Disappearance of α -TCP peaks may be due to low content of BCP in the PCL-BCP composite mat. However, α -TCP peaks were observed as BCP content increased up to 50 wt.% with mainly PCL, HAp peaks, and minor α -TCP peaks. The profiles show that crystallinity of both the organic and inorganic phase were retained in the electrospun mat. No change was observed which explains that in the electrospun mat the materials were in a physical mixture that ensures the retention of proper biocompatibility of the component.

Fig. 4 shows DSC profiles of electrospun fibrous PCL-BCP composite mats, respectively. Results of calorimetric

Fig. 4. DSC profiles of fibrous PCL-BCP composite mats (a) PCL-0 wt.% BCP, (b) PCL-30 wt.% BCP and (c) PCL-50 wt.% BCP.

Table 1. Melting point (T_m), melting enthalpy (ΔH_m), and crystallinity degree (X_c) of fibrous PCL and PCL-BCP composite mats.

Sample	T_m ($^{\circ}\text{C}$)	ΔH_m (J/g)	X_c (%)
PCL	56.2	61.6	45.3
PCL-BCP (30wt.% BCP)	60.1	54.1	39.8
PCL-BCP (50wt.% BCP)	60.7	34.8	25.6

Fig. 5. Stress-strain curves of fibrous PCL-BCP composite mats, depending on BCP contents: (a) 0 wt.%, (b) 10 wt.%, (c) 30 wt.% and (d) 50 wt.%.

Table 2. Tensile modulus (E), ultimate tensile stress ($\sigma_{\max}$), and strain at failure (ε_f) of fibrous PCL-BCP composite mats.

Sample	$\sigma_{\max}$ (MPa)	ε_f (%)	E (MPa)
PCL	0.7 ± 0.06	174 ± 20	2.3 ± 0.2
PCL-10wt.%BCP	1.3 ± 0.07	99 ± 17	5.1 ± 0.4
PCL-30wt.%BCP	0.8 ± 0.06	87 ± 5	2.8 ± 0.3
PCL-50wt.%BCP	0.3 ± 0.02	61 ± 15	1.3 ± 0.2

parameters are shown in Table 1, which show that T_m of PCL-BCP composite mats occurred at higher temperature with the neat PCL and were highest at the highest BCP content. A slightly increased T_m when loading BCP powder can be explained by interface bonding between PCL and BCP particles. On the other hand, Table 1 shows that increase of BCP content leads to decrease of crystallinity degree X_c of PCL.

Fig. 5 shows stress-strain curves of fibrous PCL-BCP composite mats, depending on BCP contents, respectively. Mechanical properties presented in Table 2 show that at 10 wt.% BCP content, tensile modulus and ultimate tensile stress of PCL-BCP composite mats reached the highest tensile modulus and ultimate tensile stress, while, they decreased when BCP content was higher than 10 wt.%. The effect of BCP contents on mechanical behavior can be explained by interface adhesion of ceramic particles and polymer. This has been explained by many researchers.^{11,14,21-23)} When content of nano ceramic particles was low, they were dispersed in the fibers as reinforcements for the polymer matrix. However, at a high content of ceramic particles, they tend to agglomerate and lead to decreasing tensile modulus and ultimate stress of PCL-BCP composite mats. Therefore, nano BCP content for distribution in fiber polymer using BCP for reinforcement

Fig. 6. SEM micrographs of low and high magnification of fracture surfaces of fibrous PCL-BCP composite mats after tensile test: (a, e) 0 wt.%, (b, f) 10 wt.%, (c, g) 30 wt.% and (d, h) 50 wt.%.

is limited. As BCP content increases, the strain at failure (ε_f) of the composites tends to decrease because flexibility of PCL mixing brittleness of BCP leads to decrease in flexibility of the composite, thus, less elongation with addition of brittleness.¹⁴⁾

Fig. 6 shows SEM morphology of electrospun PCL-BCP composite mats, depending on BCP contents, after testing of tensile strength, respectively. Fibrous morphologies, which were highly re-arranged in the stress direction, are shown. The fibrous morphology of the neat PCL was extensive and re-arranged to the stress direction at the most as shown in Fig. 6(b). This can be explained by good flexibility with high elongation at the break of the neat PCL. In other cases at 10, 30, and 50 wt.% BCP, the extensive and aligned fibrous morphology decreased. It may be explained that mixing flexibility of PCL and brittleness of BCP lead to decrease in flexibility of the composite, thus the fibers were broken before being re-arranged.

Fig. 7. Cell cytotoxicity of the diluted extract solution of fibrous PCL and PCL-BCP composite mats by MTT assay.

3.2 Cell cytotoxicity

Fig. 7 shows the cytotoxicity response of electrospun fibrous PCL-BCP composites by MTT assay. L-929 fibroblast like cells were cultured with the extract solution of each

of the four PCL-BCP composite mats for 3 days, and then assayed for cell cytotoxicity relative to the control (100% medium). Cell viability of extract solution increased slightly as increasing the content of BCP on all of concentration of extract solution. At 25% dilution survival rate for 10 wt.% BCP and 50 wt.% BCP was 82.7 ± 0.6 and 88.8 ± 2.5 respectively. The cytotoxicity difference is diminishing at higher extract dilution. The survival rate of the cells for PCL-BCP composite mats with 0, 10, 30, and 50 wt.% BCP was satisfactory at 70.9 ± 0.7 , 72.4 ± 1.9 , 73.7 ± 2.1 , and $74.5 \pm 2.1\%$ at 100% dilution, respectively. Based on cytotoxicity results, a fairly acceptable viability of the cells was observed on PCL-BCP composite mats. According to the ISO standard 10993-5, 1999 the cell viability should be more than 70% to be biocompatible, which is maintained by all the PCL-BCP composites we prepared. These results confirmed the biocompatibility of electrospun PCL and PCL-BCP composite mats.

Fig. 8. SEM micrographs of one cell morphology of L-929 fibroblast like cells on fibrous PCL-BCP composite mats, depending on BCP contents and cell incubation times.

Fig. 9. SEM micrographs of one cell morphology of MG-63 osteoblast cells on fibrous PCL-BCP composite mats, depending on BCP contents and cell incubation times.

3.3 Cell adhesion

Figs. 8 and 9 show SEM morphology of the attached L-929 fibroblast like cells and MG-63 osteoblast cells on the surface of electrospun fibrous PCL-BCP composite mats, depending on BCP contents, respectively. To confirm that muscle cell and bone cell can attach well on and biocompatible electrospun fibrous PCL-BCP mats using L-929 fibroblast-like cells and MG-63 osteoblast cells in vitro study. We perforce in vitro cell attach behavior, osteoblast cells are bone forming cell and fibroblast are musculo- varcular cells, the success of a bone scaffold are implantation can be examine by the compatibility of these two cells. Cells were shown to be well attached and proliferated on surfaces of electrospun fibrous PCL-BCP composite mats, as shown in Fig. 8 and Fig. 9, respectively. L-929 fibroblast like cells, as shown in Fig. 8(a, d, j, g), and MG-63 osteoblast cells, as shown in Fig. 9(a, d, j, g), were spherical and adhered well to the

surface of the neat PCL and PCL-BCP composite mats after 30 minutes of incubation. However, after 60 minutes of incubation, L-929 fibroblast like cells on the surface of PCL-BCP composite mats became elongated and took on a much flattened cytoplasmic form. As shown in Fig. 9(b, e, h), MG-63 osteoblast cells on PCL, PCL-10 wt.% BCP, and PCL-30 wt.% BCP mats still remained in a spherical shape, while filopodium and lamellipodium showed expansion. However, as shown in Fig. 9(k), in the case of PCL-50 wt.% BCP, MG-63 osteoblast cells adopted a spindle shaped appearance. After 90 minutes of incubation, most L-929 fibroblast like cells and MG-63 osteoblast cells had adopted a spindle shape.

As culture time increased in a range from 30 to 90 minutes, cells became more widespread, and proliferated on the surface of the mats. Compared to neat PCL at the same time, a greater area of cell spreading was observed

on PCL-BCP composites. As BCP content was increased, lamellipodium of MG-63 osteoblasts and L-929 fibroblast like cells showed greater expansion. At 50 wt.% BCP, L-929 fibroblast like cells and MG-63 osteoblast cells showed the best adherence on the surfaces of the composite mats.

BCP is known to be hydrophilic; therefore, increase of BCP content leads to increased hydrophilic surface, which is generally favorable for short-term cell adhesion.²⁴⁻²⁵⁾ On the other hand, the surface roughness of the material was affect the cell adhesion. C. Wirth²⁶⁾ have shown that fibroblast exhibited high adhesion to a smooth surface. However, osteoblast behavior is the reverse of fibroblast behavior, the roughness surface provided positive guidance for osteoblast cell to attach, leading to enhanced cellular attachment. These results are in agreement with those of our experiment. This can be explained by the fact that cell adhesion was more influenced by a hydrophilic surface than by surface roughness. Furthermore, the positive influence of calcium phosphate on the behavior of osteoblast cells has been reported.^{14,25,27-30)} Moreover, T. Matsuura et al³⁰⁾ have shown that calcium phosphate has a high adsorption capacity for serum protein.^{25,27)} Thus, as BCP content increased (3j), anchorage of MG-63 osteoblast cells improved due to adsorption of the protein onto the surface of BCP induced osteoblast cells, which were well spread (Fig. 9).

SEM morphology of attached L-929 fibroblast like cells and MG-63 osteoblast cells on the surface of electrospun fibrous PCL-BCP composite mats showed that as BCP content increased, the area of cell spreading on the surface of mats also increased. Both type of cells showed the best adherence on the surface of composite mats at 50 wt.% BCP. The cellular viability and cell adhesion data confirmed that PCL-BCP composite mats are biocompatible.

4. Conclusions

Electrospun microfibrinous PCL-BCP composite mats with varying BCP contents (0, 10, 30, 50 wt.%) were successfully fabricated. SEM micrographs show highly interconnected pores with high surface area of electrospun PCL-BCP composite mats. Their microstructures were observed to have combined micro-texture with fine and coarse fibers in the mats, without dependence on BCP contents. Fiber diameter was approximately 1 to 7 μm . As BCP increased up to 30 wt.%, the fiber's surface started to become rough, with the roughest at 50 wt.% BCP. The samples show the highest value of tensile modulus and ultimate tensile stress at 10 wt.% BCP content. The incorporation of BCP decreased the mechanical properties of the mats like the tensile modulus and ultimate tensile strength. As BCP content increased, the area of cell spreading on the surface of mats also increased. Cells showed the best

adherence on the surface of composite mats at 50 wt.% BCP for both L-929 fibroblast like cell and MG-63 osteoblast cell. The data in the present paper show that PCL-50 wt.% BCP fibrous electrospun composite was non toxic and spreading behavior was good of both type of cells, osteoblast and fibroblast cells. PCL-50 wt.% BCP fibrous electrospun composite posed as good candidates to be used as bone scaffolds.

Acknowledgements

This work was supported by Mid-career Researcher program through NRF grant funded by MEST (2009-0092808). The authors would like to express their appreciation to Ms Hiep Nguyen Thi and Mr Tuyen Van Do for their valuable technical support and assistance. The authors are grateful to Mr Swapan Kumar Sarkar for providing us with nano BCP powder and important guidelines and suggestion.

References

1. J. Zeng, X. Xu, X. Chen, Q. Liang, X. Bian, L. Yang and X. Jing, *J. Contr. Release.*, **92(3)**, 227 (2003).
2. T. B. Bini, S. Gao, X. Xu, S. Wang, S. Ramakrishna and K. W. Leong, *J. Biomed. Mater. Res. A*, **68(2)**, 286 (2004).
3. H. Yoshimoto, Y. M. Shin, H. Terai and J. P. Vacanti, *Biomaterials*, **24(12)**, 2077 (2003).
4. M. Shin, O. Ishii, T. Sueda and J. P. Vacanti, *Biomaterials*, **25(17)**, 3717 (2004).
5. M. Shin, H. Yoshimoto and J. P. Vacanti, *Tissue Eng.*, **10(1)**, 33 (2004).
6. W. J. Li, R. Tuli, X. Huang, P. Laquerriere and R. S. Tuana, *Biomaterials*, **26(25)**, 5158 (2005).
7. C. D. Gaudio, A. Bianco, M. Folini, S. Baiguera and M. Grigioni, *J. Biomed. Mater. Res.*, **89A(4)**, 1028 (2008).
8. K. A. Gross, L. M. Luis and M. R. Lorenzo, *Biomaterials*, **25(20)**, 4955 (2004).
9. G. Wei and P. X. Ma, *Biomaterials*, **25(19)**, 4749 (2004).
10. L. D. Silvio, M. J. Dalby and W. Bonfield, *Biomaterials*, **23(1)**, 101 (2002).
11. T. Vinoy, J. Sunita, J. Kalonda, J. Moncy, Y. K. Vohra, J. Nanosci. Nanotechnol., **6(2)**, 487 (2006).
12. P. Wutticharoenmongkol, N. Sanchavanakit, P. Pavasant and P. Supaphol, *Macromol. Biosci.*, **6**, 70 (2006).
13. J. R. Venugopal, S. Low, A. T. Choon, A. B. Kumar and S. Ramakrishna, *Artif. Organs*, **32(5)**, 388 (2008).
14. E. D. Federico, I. Moscatelli, A. Camaioni, I. Armentano, L. Campagnolo, M. Dottori, J. M. Kenny, G. Siracusa and G. Gusmano, *Mater. Sci. Eng.: C*, **29(6)**, 2063 (2009).
15. E. A. D. Santos, M. Farina, G. A. Soares and K. Anselme, *J. Biomed. Mater. Res.*, **89A**, 510 (2009).
16. T. P. Sastry and R. V. S. Kumar, *J. Biomater. Appl.*, **19**, 341 (2005).

17. T. J. Sill and H. A. Recum, *Biomaterials*, **29**, 1989 (2008).
18. T. Lee, M. H. Youn, R. K. Paul, K. H. Lee and H. Y. Song, *Mater. Chem. Phys.*, **104(2)**, 249 (2007).
19. G. Mickisch, S. Fajta, G. Keilhauer, E. Schlick, R. Tschada and P. Alken, *Urol. Res.*, **18(2)**, 131 (1990).
20. W. J. Li, R. L. Mauck and R. S. Tuan, *J. Biomed. Nanotechnol.*, **1(3)**, 259 (2005).
21. V. Comte, C. Lagneau, P. Exbrayat, M. Lissac, N. J. Renault and L. Ponsonnet, *Mater. Sci. Eng.: C*, **25(1)**, 51 (2005).
22. T. Matsuura, R. Hosokawa, K. Okamoto, T. Kimoto, Y. Akagawa, *Biomaterials*, **21(11)**, 1121 (2000).
23. Z. Hong, P. Zhang, C. He, X. Qiu, A. Liu, L. Chen, X. Chen, and X. Jing, *Biomaterials*, **26(32)**, 6296 (2005).
24. J. Y. Lim, M. C. Shaughnessy, Z. Zhou, H. Noh, E. A. Vogler and H. J. Donahue, *Biomaterials*, **29(12)**, 1776 (2008).
25. K. Anselme, *Biomaterials*, **21(7)**, 667 (2000).
26. A. D. Santos, M. Farina, G. A. Soares and K. Anselme, *J. Mater. Sci. Mater. Med.*, **19(6)**, 2307 (2008).
27. J. Venugopal, S. Mitra, V. R. G. Dev and S. Ramakrishna, *Biomaterials*, **30(11)**, 2085 (2009).
28. M. Ngiam, S. Liaob, A. J. Patil, Z. Chengb, C. K. Chanb and S. Ramakrishna, *Bone*, **45(1)**, 4 (2009).
29. L. Ambrosio, L. Savarino, D. Granchi, E. Cenni, N. Baldini, S. Pagani, S. Guizzardi, F. Causa and A. Giunti, *Biomaterials*, **24(21)**, 3815 (2003).
30. T. Matsuura, R. Hosokawa, K. Okamoto, T. Kimoto and Y. Akagawa, *Biomaterials*, **21(11)**, 1121 (2000).
31. S. Osawa, M. Yabe, M. Miyamura and K. Mizuno, *Polymer*, **47(11)**, 3711 (2006).