Ta Doped SnO₂ Transparent Conducting Films Prepared by PLD

Ho Je Cho, Yong Jun Seo, Geun Woo Kim, Keun Young Park,
Si Nae Heo and Bon Heun Koo[†]

School of Materials Science & Engineering, Changwon National University, Changwon 641-773, Korea

(Received July 8, 2013 : Received in revised form August 7, 2013 : Accepted August 7, 2013)

Abstract Transparent and conducting thin films of Ta-doped SnO₂ were fabricated on a glass substrate by a pulse laser deposition(PLD) method. The structural, optical, and electrical properties of these films were investigated as a function of doping level, oxygen partial pressure, substrate temperature, and film thickness. XRD results revealed that all the deposited films were polycrystalline and the intensity of the (211) plane of SnO₂ decreased with an increase of Ta content. However, the orientation of the films changed from (211) to (110) with an increase in oxygen partial pressure (40 to 100 mTorr) and substrate temperature. The crystallinity of the films also increased with the substrate temperature. The electrical resistivity measurements showed that the resistivity of the films decreased with an increase in Ta doping, which exhibited the lowest resistivity ($\rho \sim 1.1 \times 10^{-3} \Omega \cdot \text{cm}$) for 10 wt% Ta-doped SnO₂ film, and then increased further. However, the resistivity continuously decreased with the oxygen partial pressure and substrate temperature. The optical bandgap of the 10 wt% Ta-doped SnO₂ film increased (3.67 to 3.78 eV) with an increase in film thickness from 100-700 nm, and the figure of merit revealed an increasing trend with the film thickness.

Key words PLD, SnO₂, TCO, resistivity, optical properties, thin films.

1. Introduction

Nowadays, study of transparent conducting oxides(TCOs) is growing interest for material in optoelectronic devices including flat-panel displays, touch panel, heat mirrors, gas sensor, light-emitting diodes and solar cell.¹⁻⁶⁾ In particular, Sn doped In₂O₃ (ITO) is well known for widely-used TCO thin films because of the outstanding resistivity ($\rho \sim 2 \times 10^{-4} \Omega \cdot \text{cm}$) and high transmittance(80-90 %) in the visible range.⁷⁾ However, indium, which is natural resource has a shortage, thus, indium is expensive material. The alternative of ITO needs to seek indium-free TCO materials.⁸⁾ As compared to widely used ITO, SnO₂ films are chemically and thermally stabled, and also mechanically hard.⁹⁾ There are many techniques to prepare doped and un-doped SnO₂ thin films including chemical vapor deposition(CVD),¹⁰⁻¹¹⁾ spray pyrolysis,¹²⁻¹³⁾ evaporation,¹⁴⁾ sol-gel,¹⁵⁾ pulsed laser deposition(PLD)¹⁶⁾ and sputtering.¹⁷⁾ Among these, PLD technique has been used to grow various high-quality TCO thin films with low resistivity.¹⁸⁾ Also, the PLD grown films crystallize at lower substrate

temperature compare to other physical vapor deposition technique.

In the present study, we have investigated the effect of Ta doping and deposition parameters on the properties of Ta-doped SnO₂ thin films fabricated using PLD technique on glass substrate.

2. Experimental

Ta-doped SnO₂ films were deposited on glass substrates by PLD technique. A sintered Ta-doped SnO₂ ceramic target was prepared by the solid state reaction method. The stoichiometric amount of highly pure SnO₂(99.99 %) and Ta₂O₅(99.99 % purity) powders were mixed. The content of Ta₂O₅ added to the used target was varied ranging from 0-12 wt.%. Finally, the samples were ground to fine powder, pressed into pellet form, and sintered at 1250 °C for 12h followed by slow cooling(at 4 °C/min). During the deposition, laser energy density at the target surface was kept at 2 J/cm² and laser frequencies at 2 Hz. The focused laser beam was incident on the target surface at

[†]Corresponding author

E-Mail : bhkoo@changwon.ac.kr (B. H. Koo, Changwon Nat'l Univ.)

© Materials Research Society of Korea, All rights reserved.

This is an Open-Access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/3.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

an angle of 45° . The target was rotated about 10 rpm and the substrate was mounted opposite to the target at a distance of 45 mm. After deposition, the thin films were cooled slowly to room temperature at the rate of $5^\circ\text{C}/\text{min}$. The film thickness was measured by a stylus profilometer. The structural properties of the films were analyzed by X-ray diffraction (XRD) (Cu $K\alpha 1$, $\lambda = 0.154 \text{ nm}$) and the scans were performed with 0.02° step size in the 2θ range of 20 – 80° . Morphological studies were carried out using FESEM (MIRA II; LMH) microscope. Electrical properties were measured by a four-point probe sheet resistance (Mitsubishi Loresta MCP-T610 TFP probe) and Hall measurement. The optical properties of films were studied at room temperature with a UV-VIS-NIR spectrometer in the wavelength range of 300 – 800 nm .

3. Results and Discussion

Fig. 1(a) shows the XRD patterns for undoped and Ta-doped SnO_2 films grown on glass substrates at 500°C in 60 mTorr of oxygen partial pressure. It can be seen from Fig. 1(a) that all the films are polycrystalline in nature with tetragonal structure. It is also noted that high intensity

Fig. 1. (a) X-ray diffraction patterns and (b) electrical properties for the Ta doped SnO_2 films grown on glass substrate with different composition.

peak corresponding to the (211) plane is observed for the undoped SnO_2 film which is well matched with the standard SnO_2 (JCPDS 88-0287). The intensity of (211) plane decreased with the increase of Ta doping in SnO_2 while, the intensity of (110) plane was found to increase with Ta doping. No secondary phase was detected within the detection limit of XRD implied that the Ta dopant was successfully incorporated in SnO_2 .

Fig. 1(b) shows the variation of electrical resistivity (ρ), carrier concentration (n), and Hall mobility (μ) of Ta-doped SnO_2 films as a function of Ta content in the targets used for deposition. It is observed that the carrier concentration increasing with the increase of Ta₂O₅ content until 10 wt.% and then above 10 wt.%, the carrier concentration nearly get saturate. Because of increase in free carrier concentrations as a result of the donor electrons from the dopant (Ta), the resistivity decreased with the increase in doping level of 0 to 10 wt.%. The initial carrier concentration of the Ta doped SnO_2 films increased because of the substitutional incorporation of Ta⁵⁺ ions at Sn⁴⁺ cation site or incorporation of Ta⁵⁺ cations in interstitial position. This result is in good agreement with the previous study on the Sb doped SnO_2 films.⁹⁾ However, it is indicating that Hall mobility decreasing with increasing Ta content, caused by ionized impurity scattering and grain boundary scattering.¹⁹⁾ Therefore, the resistivity decreased as the Ta content was increased, reached the lowest value with a Ta content of 10 wt.%(Ta₂O₅), and then increased with a further increase of Ta content.

The substrate temperature (T_s) and oxygen partial pressure during deposition were suggested to be the key parameters for growing TCO thin films.²⁰⁾ Fig. 2(a) shows the XRD patterns of Ta-doped SnO_2 films grown with different oxygen partial pressure on glass substrates at 500°C . The intensity of the peak corresponding to the (110) plane is increasing with oxygen partial pressure, while those for (211) is decreasing. Consequently, the orientation of the films changed from (211) to (110) plane with the increase of oxygen partial pressure.

Fig. 2(b) shows the electrical resistivity, carrier concentration, and Hall mobility as a function of the oxygen partial pressure for Ta doped SnO_2 films deposited at 500°C of substrate temperature. The oxygen partial pressure was found to affect the resistivity of the films. The carrier concentrations of the Ta-doped SnO_2 films deposited in oxygen partial pressure is related to the number of oxygen vacancies. The free electrons were created by oxygen vacancies in the films because one oxygen vacancy creates two extra electrons in the film. The increase in the number of oxygen vacancies leads to an increase in carrier concentration. According to the increase of oxygen partial pressure, deficiencies (oxygen vacancies) were decreased with improving the crystallinity as seen in the Fig

Fig. 2. (a) X-ray diffraction patterns and (b) electrical properties for the Ta doped SnO₂ films grown on glass substrate in different oxygen pressure.

2(a). As a result, the mobility of carriers was increased with decreasing the resistivity of the Ta-doped SnO₂ films. Therefore, resistivity decreases with the oxygen partial pressure from 20 to 60 m Torr, reaches a minimum at 60 m Torr ($\rho \sim 1.1 \times 10^{-3} \Omega \cdot \text{cm}$), and then increases above 60 m Torr.

Fig. 3(a) shows the XRD patterns of the Ta-doped SnO₂ films as a function of different substrate temperatures with a doping of 10 wt.%(Ta₂O₅). It can be seen that the films deposited at RT and 100 °C are amorphous in nature, while films deposited at 300 to 600 °C of substrate temperatures showed a polycrystalline structure. The crystallinity of the films increased with the increase of substrate temperature. It is also clear from SEM images shown in Fig. 4(a) and 4(b); film deposited at 500 °C of substrate temperature shows more dense and crystalline structure. Complemented with the effect of oxygen partial pressure on the orientation of films, the increase in substrate temperature also changed the orientation from (211) to (110) plane.

Fig. 3(b) shows the variation of electrical resistivity with the substrate temperatures. The resistivity decrease from 8.7×10^{-1} to $1.1 \times 10^{-3} \Omega \cdot \text{cm}$ with increasing sub-

Fig. 3. (a) X-ray diffraction patterns and (b) electrical properties for the Ta doped SnO₂ films grown on glass substrate at different substrate temperature.

strate temperature from room temperature(RT) to 500 °C and then becomes almost constant upon further increasing the temperature to 600 °C. This decrease in resistivity may be due to an increase in diffusion of Ta atoms from interstitial locations and grain boundaries in to the Sn⁴⁺ cation sites. Since, Ta atom has a valency of 5+ and Sn has 4+, Ta atoms act as donors in Ta-doped SnO₂ films. Hence, the increase in diffusion with the substrate temperature results in higher electron concentration. The decrease in the resistivity with increase in deposition temperature can be also explained by the crystallinity of films improves with increasing the deposition temperature. The crystallinity of films can cause a decrease in grain boundary scattering, which lead to increase in the conductivity.

Fig. 5(a) shows the X-ray diffraction patterns of 10 wt.%(Ta₂O₅) Ta doped SnO₂ films with different thickness. It is observed that films with higher thickness are more crystalline than the thinner films. Fig. 5(b) shows the electrical properties(ρ , n , μ) as a function of film thickness of the films grown from the Ta doped SnO₂ target at 500 °C and 60 m Torr of oxygen partial pre-

Fig. 4. Cross-sectional FE-SEM image of the Ta doped SnO_2 films: (a) T_s = room temperature and (b) T_s = 500 °C.

Fig. 5. (a) X-ray diffraction patterns and (b) electrical properties for the Ta doped SnO_2 films grown on glass substrate with different thickness.

ssure. The film thickness is directly proportional to the number of laser shots with an average deposition rate of 0.07 nm/shot. It is seen from Fig. 5(b) that carrier concentration and Hall mobility increases with increasing film thickness from 100 to 300 nm and then above 300 nm, nearly gets saturate. The crystallinity of films can cause a decrease in grain boundary scattering, which lead to

Fig. 6. (a) Transmittance and (b) absorbance for the Ta doped SnO_2 films grown on glass substrate with different thickness.

decrease in the resistivity. Thus, the resistivity of the Ta-doped SnO_2 films initially decreases with an increase in the film thickness until 300 nm ($1.1 \times 10^{-3} \Omega\cdot\text{cm}$) and remains almost constant until 700 nm. For thicker films ($> 300 \text{ nm}$), the resistivity remains constant because both carrier concentration and mobility become independent of film thickness.²¹⁾

Fig. 6(a) shows the transmittance spectra of the Ta-doped SnO_2 films deposited at 500 °C and 60 m Torr of oxygen partial pressure with different thickness in the

Fig. 7. The Tauc plots ($n = 1/2$) of Ta doped SnO₂ thin films with different thickness.

Fig. 8. The figure of merit of the Ta doped SnO₂ thin films as functions of films thickness.

visible region. The average transmittance in the visible region was observed between 79 to 82 %, whatever thickness of films.

Highest value of transmittance is observed to be 82 % for the film heat treated at 500 °C and this is attributed to the low scattering effect and uniform film thickness caused by smooth and good surface texture of the film.

Consequently, all films exhibited high transparency in the visible region. The absorption spectra as shown in Fig. 6(b) of all films were almost identical and exhibit low absorption in the visible region. Therefore, we conclude that thickness of the films does not show considerable effect on the transparency.

All the above investigations and the interpretations depict that Ta doped SnO₂ thin films of good reproducibility and excellent optoelectronic properties can be obtained by PLD method at the optimum heat treatment temperature 500 °C and 60 mTorr of oxygen partial pressure which can be used as a potential TCO.

Fig. 7 shows the optical band gap plot of $(\alpha hv)^{1/2}$ vs $h\nu$ for Ta-doped SnO₂ thin films with various film thickness. The optical band gap (E_g) of the films was determined by extrapolating the linear region of $(\alpha hv)^{1/2}$ vs $h\nu$ plots. The E_g (direct allowed) of the Ta-doped SnO₂ is found to increase from 3.67 to 3.78 eV with an increase in the film thickness, as shown in Fig. 7. Thus, Ta doped SnO₂ films show a blue shift in band gap energy with an increase in the film thickness.

Fig. 8 shows a significant factor for estimating TCO thin films in relation to their applications. Conductivity and transmittance are inversely proportional to each other and should be as high as possible for effective usage. The figure of merit is widely used to compare the performance of various transparent conductors as first defined by Haacke²²⁾ is, $\Phi = Tr/10/R_s$ where Tr is the optical transmittance for the range of 400–800 nm and R_s is the sheet resistance. Fig. 8 shows the plot of figure of merit vs. film thickness of Ta doped SnO₂ films. The figure of merit increases consistently because of increase in films thickness. This can be explained as follows: usually in thin films the resistivity depends on film thickness.

4. Conclusions

Transparent conducting Ta doped SnO₂ thin films on glass substrate have been successfully deposited by using pulsed laser deposition and examined the dependence of their structural, electrical and optical properties on the deposition parameters and Ta content. The doping level, oxygen partial pressure, substrate temperature and film thickness were optimized to fabricate the most conductive Ta doped SnO₂ thin film. XRD results showed that all the deposited films were polycrystalline and the intensity of (211) plane of SnO₂ decreased with the increase of Ta content. With the increase in oxygen partial pressure (40 to 100 mTorr) and substrate temperature, the orientation of the films changed from (211) to (110). Also, the enhancement in the crystallinity of the doped films with the increase of substrate temperature was observed. The electrical resistivity measurements showed that the resistivity of the films was found to decrease with the increase of Ta doping exhibited lowest resistivity ($\rho \sim 1.1 \times 10^{-3} \Omega\cdot\text{cm}$) for 10 wt% Ta-doped SnO₂ film and then further increase. However, the resistivity was continuously decreased with oxygen partial pressure and substrate temperature. For 300 nm thick SnO₂:Ta film deposited at 500 °C and 60 m Torr of oxygen partial pressure, an electrical resistivity $1.14 \times 10^{-3} \Omega\cdot\text{cm}$ with an average optical transmittance in visible range (400–800 nm) of 82 % were observed. The presented study will provide the ability to grow Ta doped SnO₂ films with low resistivity and high optical transmission by PLD technique. It is

expected that Ta doped SnO₂ are an important indication for the further improvement of device.

Acknowledgments

This research was supported by the MSIP(Ministry of Science, ICT & Future Planning), Korea, under the ITRC (Information Technology Research Center) support program supervised by the NIPA(National IT Industry Promotion Agency) (NIPA-2013-H0301-13-2009). This research was financially supported by the Ministry of Education, Science Technology(MEST) and National Research Foundation of Korea(NRF) through the Human Resource Training Project for Regional Innovation(2012H1B8A 2026212).

References

1. P. S Patil, P. K. Kavar, S. B. Sadale, P. S. Chigare, Thin Solid Films **437**, 34 (2003).
2. Laverty S. J., Feng H., Mauire P., J. Electrochem Soc. **144**, 2165 (1997).
3. W. A. Badway, H. H. Afifi, and E. M. Elgari, J. Electrochem. Soc. **137**, 1592 (1990).
4. D. S Ginely and C. Bright, Mater. Res. Bull. **25**, 15 (2000).
5. R. Lalauze, P. Breuil, C. Pijolat, Sensor Actuators **B7**, 709 (1992).
6. Y. k. Fang, J. J. Lee, Thin Solid Films **169**, 51 (1989).
7. K. L. Chopra, S. Major, D. K. Pandya, Thin Solid Films **102**, 1 (1983).
8. Matthew S. Dabney, Maikel F. A. M. van Hest, Charles W. Teplin, S. Phil Arenkiel, John D. Perkins, David S. Ginley Thin Solid Films **516**, 4133 (2008).
9. H. Kim and A. Pique App. Phys. Lett. **84**, 218 (2004).
10. A. Martín, J. P. Espinós, A. Justo, J. P. Holgado, F. Yubero, A. R. González-Elipe, Surf. Coat. Tech. **151-152**, 289 (2002).
11. R. M. Ataev, A. M. Bagamadova, A. M. Djabrailov, V. V. Mamedov, R. A. Rabadanov, Thin Solid Films **260**, 19 (1995).
12. M. T. Mohammad, A. A. Hashimb, M. H. Al-Maamoryc, Materials Chemistry and Physics **99**, 382- (2006).
13. Takashi Ogi, DarmawanHidayat, Ferry Iskandar, Agus Purwanto, KikuoOkuyama, Advanced Powder Technology **20**, 203 (2009).
14. A. Amaral, P. Brogueira C. Nunes de Carvalho, G. Lavareda, Surf.Coat. Tech. **125**, 151 (2000).
15. C. Terrier, J. P. Chatelon, J. A. Roger, Thin Solid Films **295**, 95 (1997).
16. F. K. Shan, G. X. Liu, W. J. Lee, G. H. Lee, I. S. Kim, B. C. Shin, Y. C. Kim, J. Crystal Growth **277**, 284 (2005).
17. X. Bie, J. G. Lu, L. Gong, L. Lin, B. H. Zhao, Z.Z. Ye, Applied Surface Science **256**, 289 (2009).
18. H. Kim, J. S. Horwitz, G. P. Kushto, Z. H. Kafafi, and D. B. Chrisey, Appl. Phys. Lett. **79**, 284 (2001).
19. B. Thangaraju, Thin Solid Films **402**, 71 (2002).
20. K. Tonooka, Te-Wei Chiu, N. Kikuchi, Appl. Surf. Sci. **255**, 9695 (2009).
21. H. Kim, C. M. Gilmore, A. Piqué, J. S. Horwitz, H. Mattoussi, H. Murata, Z. H. Kafafi, and D. B. Chrisey, J. Appl. Phys. **86**, 6451 (1999).
22. R. J. Deokate, S. V. Salunnkhe, G. L. Agawane, B. S. Pawar, S. M. Pawar, K. Y. Rajpure, A. V. Moholkar, J. H. Kim, J. Alloys Compd. **496**, 357 (2010).