Point Defects and Photoluminescence of Green Phosphors

$\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ and $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^+$

Seon-Woog Cho[†]

Department of Materials Science and Engineering, Silla University, Busan 617-736, Korea

(Received August 14, 2013 : Received in revised form September 10, 2013 : Accepted September 10, 2013)

Abstract Two types of Tb- and Na-substituted green phosphors $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ and $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^+$ were synthesized with various x values, using a solid-state reaction. The former phosphors contained both substitutional and vacancy point defects, while the later had only substitutional defects. X-ray diffraction results showed that the main diffraction peak, (112), was centered at $2\theta = 28.72^\circ$ and indicated that there was no basic structural deformation caused by substitutions or vacancies. The photoluminescence emission and photoluminescence excitation spectra revealed the optical properties of trivalent terbium ions, Tb^{3+} . Typical transitions, $^5D_3 \rightarrow ^7F_6, ^7F_5, ^7F_4$ and $^5D_4 \rightarrow ^7F_6, ^7F_5, ^7F_4, ^7F_3$, and cross relaxations were observed. Subtle differences in the photoluminescence of green phosphors were observed as a result of the point defects. The FT-IR spectra indicated that some of the ungerade vibrational modes had shifted positions and changed shapes, spreading out over a wide range of frequencies. This change can be attributed to the different masses of Tb^{3+} and Na^+ ions and V_{Ca} vacancies compared to Ca^{2+} ions. The gerade normal modes of the Raman spectra exhibited subtle differences resulting from point defects in $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$.

Key words scheelite CaWO_4 , $\text{Ca}_{(1-1.5x)}\text{Tb}_x^{3+}\text{WO}_4$, $\text{Ca}_{(1-2x)}\text{Tb}_x^{3+}\text{Na}_x^+\text{WO}_4$, green phosphor, point defect.

1. Introduction

In a series of previous papers,^{1,2)} we presented the physical properties of red phosphors $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Eu}_x^{3+}$ and $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Eu}_x^{3+}, \text{Na}_x^+$. We have seen some distinctions of point defects, i.e. vacancies and substitutions, through pycnometric and spectroscopic studies. Here in this work we report the point defects and photoluminescence of green phosphors $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ and $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^+$. Scheelite CaWO_4 itself is a very efficient luminescent material at room temperature, and is used commercially as X-ray phosphor.^{3,4)} Terbium can be substituted for Ca^{2+} in scheelite as trivalent Tb^{3+} ions. The substitution of trivalent Tb^{3+} for divalent Ca^{2+} requires a charge compensating mechanism to maintain electrical neutrality. If it enters as trivalent Tb^{3+} , it enters scheelite by either the vacancy V_{Ca} or alkaline (such as Na^+) coupled substitution mechanism:

and

in Kröger-Vink notation,⁵⁾ respectively. Mechanism (1) produces one vacancy V_{Ca}'' for every substitution of two Tb^{3+} ions into three Ca^{2+} sites. However, in mechanism (2) one Tb^{3+} ion and one Na^+ ion occupy two Ca^{2+} sites, individually. So both mechanisms (1) and (2) satisfy the charge balance as well as site balance, which should be fulfilled in defect chemistry.

One of the main purposes of this paper is to disclose point defects, such as vacancies or substitutions, in the green phosphors $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ and $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^+$. Then we will see how the different nature of defects appears in the photoluminescence. Both (1) and (2) mechanisms, being efficient charge compensations, create point defects, and result in as an enhanced luminescence.^{1,2,6)} For mechanism (2), we selected sodium among candidate alkali metal elements because of its similarity with calcium in size as well as other chemical properties such

[†]Corresponding author

E-Mail : swcho@silla.ac.kr (S. -W. Cho, Silla University)

© Materials Research Society of Korea, All rights reserved.

This is an Open-Access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/3.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

as electronegativity. The similarity between Na^+ and Ca^{2+} is understood as an example of diagonal relationships⁷⁾ that exist in the periodic table.

2. Experimental

Using the solid-state reaction method we reported previously in Ref. 2, $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ were synthesized with various Tb^{3+} contents, x . The concentrations of terbium were $x = 0.005, 0.010, 0.015, 0.020, 0.025$, and 0.030 . All the starting chemicals were purchased from Sigma-Aldrich Korea. Heating and cooling rates were less than $4^\circ\text{C}/\text{min}$. In the mean time of heating, 3 hours setting at 350°C were provided to allow enough time for terbium(III,IV) oxide Tb_4O_7 to change into another form of terbium(III) oxide Tb_2O_3 . Terbium (III,IV) oxide can thermally decompose to terbium (III) oxide according to the reaction of Tb_4O_7 (dark brown) $\rightarrow 2\text{Tb}_2\text{O}_3$ (white) + $(1/2)\text{O}_2$.^{8,9)} Basic scheme of the synthesis is calcination of CaCO_3 to intermediate CaO , then CaO and WO_3 combine to form CaWO_4 . Following calcination, the highest temperature reached up to $1,100^\circ\text{C}$ and stayed there for 4 hours for $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$. This temperature was lowered to 950°C for $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$, because we found that they form partly fused clusters of powder on a high temperature. The chemical reactions are as follows:

and

Crystal structure was determined by a X-ray diffractometer, Philips PANalytical X'Pert PRO MPD. Optical properties were studied by photoluminescence excitation (PLE) and photoluminescence(PL) emission spectroscopy using a fluorescence spectrometer, Scinco FS-2. Also presented are the Fourier transform infrared(FT-IR) and Raman studies of the green phosphors(Vertex 80 V, Bruker).

3. Results and Discussion

Fig. 1 shows the XRD spectra of $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ ceramic powders. The XRD spectra of the $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ samples were essentially the same as the $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ results, so they are not presented here. The XRD patterns of the prepared phosphors correspond to the International Centre for Diffraction Data (ICDD) Powder Diffraction

Fig. 1. XRD patterns of $\text{Ca}_{(1-1.5x)}\text{Tb}_x^{3+}\text{WO}_4$ samples with various x values, and the pattern of CaWO_4 , ICDD PDF 41-1431.

File (PDF) 41-1431, without showing any significant difference on the concentration x of Tb. Diffraction angles 2θ for the planes (101), (112), (004), (200), (211), (204), (116), (312), and (316) are $18.61^\circ, 28.72^\circ, 31.43^\circ, 34.17^\circ, 39.18^\circ, 47.10^\circ, 54.31^\circ, 57.88^\circ$, and 76.22° , respectively. It belongs to the body-centered tetragonal system and space group $I4_1/a$.

Figs. 2(a) and 2(b) present the expanded version of XRD spectra in the range of diffraction angle $2\theta = 27^\circ$ to 30° . The main peaks at 28.72° correspond to (112) planes, and the peaks at 29.04° represent (103) planes. The smaller shoulder peaks nearby those two peaks are probably traces of unreacted reactants or intermediates CaCO_3 , WO_3 , etc. leftover in the products after synthesis. Not reacted excess CaCO_3 , CaO , or WO_3 are readily diffused in CaWO_4 in small amounts and permit growth despite the undesired nonstoichiometry in the semi-liquid melt stage.¹⁰⁾ Calcium carbonate CaCO_3 has its main (104) peak at $2\theta = 29.072^\circ$ (PDF 86-2343). We found little difference in the d-spacing values of the (112) planes due to the distinct ionic radii among Ca^{2+} (112 pm), Tb^{3+} (104 pm), and Na^+ (118 pm).¹¹⁾ If we follow Vegard's law,¹²⁾ the lattice parameter of the solid solution is directly proportional to the atomic percentage of solute present. However, the positions of main

Fig. 2. (a) Expanded version of XRD spectra of $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ with various x values of terbium ions Tb^{3+} , from $2\theta = 27^\circ$ to 30° , (b) Expanded XRD spectra of $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^{+}$ with various x values of Tb^{3+} and Na^{+} ions. Also marked is ICDD PDF 41-1431 pattern of CaWO_4 .

Fig. 3. (a) Excitation spectra of the $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ samples, (b) Excitation spectra of the $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^{+}$ samples.

peak at $2\theta = 28.72^\circ$ practically do not move at all even after the substitution with increased value of x . We are not surprised in the case of Na co-doped $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$, because the sum of two calcium ions almost nicely matches with the sum of terbium and sodium ions in matter of size. On the other hand, we are phenomenologically led to a conclusion from the results of $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$, in which x Tb^{3+} ions replace $(3/2)x$ Ca^{2+} ions creating $(1/2)x$ V_{Ca} vacancies. If the lattice does not shrink around a missing Ca^{2+} ion, we can estimate the size of vacancy V_{Ca} that replaces the calcium site from the difference between the radii of Ca^{2+} and Tb^{3+} as follows: $3r_{\text{Ca}^{2+}} = 2r_{\text{Tb}^{3+}} + r_{V_{\text{Ca}}}$. Using effective ionic radii from Shannon¹¹⁾ for eight-fold coordination we obtain the radius of vacancy: $r_{V_{\text{Ca}}} = 3r_{\text{Ca}^{2+}} - 2r_{\text{Tb}^{3+}} = 3(112 \text{ pm}) - 2(104 \text{ pm}) = 128 \text{ pm}$. This number suggests that in $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ the cation vacancies have its own rather roomy space with some size. Vegard's law is simply an expression of the idea that the cell parameters are a direct consequence of the sizes of the component atoms in the

solid solution. The ideal form of Vegard's law is not obeyed here. Atomic interactions, which offset the size effects, are responsible for this deviation.¹³⁾ It is tempting to assume that a lattice will shrink around a vacancy, but it must be kept in mind that the removal of a cation causes the nearest neighbor anions to experience increased electrostatic repulsion from one another, unshielded by the cation.¹⁴⁾

Figs. 3(a) and 3(b) show excitation spectra of $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ phosphors. The PLE spectra of these systems ($\lambda_{\text{em}} = 546 \text{ nm}$ and 545 nm , respectively) consist of a broad band and some weak lines: (1) The broad band 220–300 nm is attributed to $\text{O}^{2-} \rightarrow \text{W}^{6+}$ ligand to metal charge transfer (LMCT)¹⁵⁾ and energy transfer from WO_4^{2-} group to the Tb^{3+} ions¹⁶⁾ showing maximum at 266 nm and 262 nm, respectively. These different positions of maxima may be resulted in by the small difference of hardness of lattice structure between a sparsely vacant type $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and a fully occupied type $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$. (2) In addition to this broad and

Fig. 4. (a) PL emission spectra of $\text{Ca}_{(1-1.5x)}\text{WO}_4:\text{Tb}_x^{3+}$ phosphors, (b) PL emission spectra of $\text{Ca}_{(1-2x)}\text{WO}_4:\text{Tb}_x^{3+}, \text{Na}_x^+$ phosphors.

strong LMCT, the f - f transitions within the $\text{Tb}^{3+} 4f^8$ configuration are observed with weak intensities at longer wavelengths. The small peak at 318 nm is ascribed to the transitions from the ground state 7F_6 to a higher energy level 5D_0 .^{16,17)} Regarding the ground state term symbol, for electron configurations with a more than half filled shell the multiplet with largest $L+S=J$ (for example, in $4f^8$ 7F terms, $3+3=6$) is the lowest state, following Hund's third rule.¹⁸⁾ Even though the concentration quenching appears to start at around $x=0.025$ for both formulae, we found from Figs. 3(a) and 3(b) some delicate discrepancy between $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ in optical excitation, with small difference of maximum positions.

In PL emission, Figs. 4(a) and 4(b), we found some differences between $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ regarding their photoluminescence characteristics. Both show typical transitions $^5D_3 \rightarrow ^7F_6, ^7F_5, ^7F_4$ and $^5D_4 \rightarrow ^7F_6, ^7F_5, ^7F_4, ^7F_3$ of Tb^{3+} , having peaks at 382, 414, 437 nm for the former set and 489, 546(545), 588, 622 nm for the latter set, respectively. Emission from 5D_4 to $^7F_J (J=6, 5, 4, 3, 2, 1, 0)$ are stronger than those from 5D_3 to 7F_J . This may attributed to the cross-relaxation of Tb^{3+} ions.^{3,17,19,20)}

Electrons in 5D_3 relax to 5D_4 , then electrons in 7F_6 of neighboring Tb^{3+} are excited to 7F_0 . The cross-relaxation between two adjacent Tb^{3+} ions weakens the $^5D_3 \rightarrow ^7F_J$ transitions and enhances the $^5D_4 \rightarrow ^7F_J$ transitions at the same time. In the range of wavelength $483 \text{ nm} < \lambda < 650 \text{ nm}$, the concentration quenching occurs to start at around $x=0.025$ for both formulae. However, in $320 \text{ nm} < \lambda < 483 \text{ nm}$, the x values for concentration quenching are different. It starts at $x=0.01$ for $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$, but it appears at a later stage of $x=0.02$ for $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$. We understand that cross-relaxation and concentration quenching are both examples of energy transfer of identical luminescent centers³⁾ (between Tb^{3+} and another nearby Tb^{3+} in this case). It seems that energy migration in a vacancy included $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ starts at slightly earlier stage of concentration x than in a fully occupied $\text{Ca}_{(1-2x)}$

Fig. 5. FT-IR spectra of CaWO_4 , $\text{Ca}_{0.9625}\text{Tb}_{0.025}\text{WO}_4$, and $\text{Ca}_{0.95}\text{Tb}_{0.025}\text{Na}_{0.025}\text{WO}_4$.

Fig. 6. Raman spectra of CaWO_4 , $\text{Ca}_{0.9625}\text{Tb}_{0.025}\text{WO}_4$, and $\text{Ca}_{0.95}\text{Tb}_{0.025}\text{Na}_{0.025}\text{WO}_4$.

$\text{Tb}_x\text{Na}_x\text{WO}_4$, which has only substitutional point defects. Also we see an overlapped broad band envelope covering 340-540 nm, a remnant emission of host CaWO_4 .^{1,19,20)}

Fig. 5 presents the FT-IR spectra of CaWO_4 , $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$, and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$. And Fig. 6 shows the

Raman spectra of CaWO_4 , $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$, and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$. Here we present only $x = 0.025$ cases, because this is the concentration showing the highest luminous intensity. The CaWO_4 crystals have twenty-six distinct vibrational modes.^{2,21)} Among these, eight vibrational modes are IR active $\Gamma_{\text{IR}} = 4A_u + 4E_u$, and thirteen modes are expected to be Raman active $\Gamma_{\text{Raman}} = 3A_g + 5B_g + 5E_g$. Here the subscripts u (ungerade) and g (gerade) indicate the parity under inversion in centrosymmetric crystals CaWO_4 .

In the host material calcium tungstate ($\text{Ca}^{2+}\text{WO}_4^{2-}$), the Ca^{2+} ions are eight-fold coordinated to oxide ions from eight separate WO_4^{2-} tetrahedra. It can, therefore, be regarded as being composed of clusters of $[\text{CaO}_8]$ and $[\text{WO}_4]$. Calcium and tungsten atoms do not bond directly, so the bonding sequence is -Ca-O-W-O- throughout the whole crystal. IR results in Fig. 5 reveal that ungerade vibrations are very different after the replacement of Ca^{2+} . The positions of $E_u + A_u$, E_u , and A_u modes in CaWO_4 are 439, 754, and 822 cm^{-1} , respectively.²⁾ The E_u and A_u vibrations of 754 and 822 cm^{-1} drastically change following the substitution. Both peaks become swollen bands spreading over wide range of frequencies. These deformations seem more severe in the blue curve ($\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$) than the red ($\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$). We suggest, based on the data presented in Fig. 5, that the bonding sequences -Tb-O-W-O-, -Na-O-W-O-, and $-\text{V}_{\text{Ca}}\text{-O-W-O-}$ created by the substitution of Ca^{2+} with Tb^{3+} , etc. disrupt the bonding sequence of the host crystal CaWO_4 and appear as antisymmetric ungerade vibrations in $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$. This local distortion is more sensitive in $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$, in which both vacancies and substitutional point defects co-exist, than in $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$, in which only substitutional point defects fully occupy all the site with different masses.

The Raman spectra presented in Fig. 6 show that the frequencies of all the gerade modes are unchanged upon replacement of Ca^{2+} with Tb^{3+} , Na^+ , or V_{Ca} , but showing somewhat lower intensities. The positions and shapes of the Raman peaks are very similar those observed by Gracia, et al.²²⁾ and Cavalcante, et al.²³⁾ obtained from differently synthesized CaWO_4 crystals. Here we note, again, that the blue curve ($\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$) shows less intense peaks than the red ($\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$), although the peaks of both appear at identical positions and have similar shapes. This observation leads us to conclude that, for gerade vibrations, different types of points defects produce different Raman intensities.

4. Conclusion

Using a solid-state reaction, two kinds of green ceramic phosphors $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ were

synthesized with various concentrations of Tb^{3+} ions. XRD results showed that there was no structural shrinkage due to the Tb^{3+} or Na^+ ions, or the vacancies V_{Ca} . Point defects, especially vacancies, were detected successfully through XRD and spectroscopic measurements.

We estimated the size of the vacancies in the $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ samples to be $r_{\text{V}_{\text{Ca}}} = 128\text{ pm}$. PL emission spectra showed typical transitions $^5D_3 \rightarrow ^7F_6, ^7F_5, ^7F_4$ and $^5D_4 \rightarrow ^7F_6, ^7F_5, ^7F_4, ^7F_3$ of trivalent Tb^{3+} ions with cross relaxations. We found that the nature of point defects is delicately related to photoluminescence and the energy transfer mechanisms of these green phosphors. FT-IR spectra showed that, due to the different masses of Tb^{3+} and Na^+ ions, and V_{Ca} vacancies compared to Ca^{2+} , some of the ungerade normal modes had shifted positions and different shapes. The $[\text{TbO}_8]$, $[\text{NaO}_8]$, and $[\text{V}_{\text{Ca}}\text{O}_8]$ clusters created within after the substitution of Ca^{2+} with Tb^{3+} , Na^+ , and V_{Ca} resulted in symmetry breaking of the host crystal CaWO_4 , which appeared as antisymmetric ungerade vibrations in both $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ and $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ samples. Raman spectra revealed that, without showing any difference before and after the doping of activators to the host material CaWO_4 , all the gerade normal modes occur at identical frequencies with the same shapes and diminished peak intensities after substitution. Intensity weakening was more apparent in the $\text{Ca}_{(1-1.5x)}\text{Tb}_x\text{WO}_4$ samples, which contained $(1/2)x$ vacancies, than in the $\text{Ca}_{(1-2x)}\text{Tb}_x\text{Na}_x\text{WO}_4$ samples, which had no vacancies.

Acknowledgements

The XRD and FT-IR/Raman spectra were obtained using the facilities of Korea Basic Science Institute (KBSI). The author is grateful to Professor Shinho Cho (Silla University) for his suggestion at an early stage of this study. He also thanks his student Jun Lee for producing neat and clear figures for this paper.

References

1. S. Cho and S. -W. Cho, Kor. J. Mater. Res., **22**, 215 (2012) (in Korean).
2. S. -W. Cho, Bull. Korean Chem. Soc., **34**(9), 2769 (2013).
3. G. Blasse and B. C. Grabmaier, Luminescent Materials, Springer-Verlag, Berlin, Germany, (1994).
4. T. E. Warner, Synthesis, Properties and Mineralogy of Important Inorganic Materials, p. 228-239, John Wiley and Sons, U. K., (2011).
5. N. G. Connelly, T. Damhus, R. M. Hartshorn and A. T. Hutton, Nomenclature of Inorganic Chemistry, IUPAC Recommendations 2005, p. 238-241, RSC Publishing, Cambridge, U. K., (2005).
6. S. Shi, J. Gao and J. Zhou, Optical Materials, **30**, 1616 (2008).

7. P. Atkins, T. Overton, J. Rourke, M. Weller and F. Armstrong, *Inorganic Chemistry*, 4th ed., p.259, Oxford University Press, Oxford, U. K., (2006).
8. Z. C. Kang and L. Eyring, *J. Alloy. Compd.*, **249**, 206 (1997).
9. G. Qiu, D. Wang, X. Jin and G. Z. Chen, *Electrochimica Acta*, **51**, 5785 (2006).
10. K. Nassau and G. M. Loiacono, *J. Phys. Chem. Solids*, **24**, 1503 (1963).
11. R. D. Shannon, *Acta Cryst.*, **A32**, 751 (1976).
12. B. D. Cullity and S. R. Stock, *Elements of X-Ray Diffraction*, 3rd ed., p.339, Prentice Hall, U. S. A., (2001).
13. R. J. D. Tilley, *Defects in Solids*, p. 13-14, John Wiley & Sons, U. S. A., (2008).
14. Y. -M. Chiang, D. Birnie, III and W. D. Kingery, *Physical Ceramics* p.131, John Wiley & Sons, U. S. A., (1997).
15. C. A. Kodaira, H. F. Brito and M. C. F. C. Felinto, *Journal of Solid State Chemistry*, **171**, 401 (2003).
16. J. Liao, B. Qiu, H. Wen and W. You, *Optical Materials*, **31**, 1513 (2009).
17. H. Wu, Y. Hu, F. Kang, L. Chen, X. Wang, G. Ju and Z. Mu, *Materials Research Bulletin*, **46**, 2489 (2011).
18. B. Di Bartolo, *Optical Interactions in Solids*, 2nd ed., p.188, World Scientific, Singapore, (2010).
19. E. Cavalli, P. Boutinaud, R. Mahiou, M. Bettinelli and P. Dorenbos, *Inorg. Chem.*, **49**, 4916 (2010).
20. Y. Tian, B. Chen, H. Yu, R. Hua, X. Li, J. Sun, L. Cheng, H. Zhong, J. Zhang, Y. Zheng, T. Yu and L. Huang, *Journal of Colloid and Interface Science*, **360**, 586 (2011).
21. D. L. Rousseau, R. P. Bauman and S. P. S. Porto, *J. Raman Spectrosc.*, **10**, 253 (1981).
22. L. Gracia, V. M. Longo, L. S. Cavalcante, A. Beltran, W. Avansi, M. S. Li, V. R. Mastelaro, J. A. Varela, E. Longo and J. Andrs, *J. Appl. Phys.*, **110**, 043501 (2011).
23. L. S. Cavalcante, V. M. Longo, J. C. Sczancoski, M. A. Almeida, J. A. Batista, J. A. Varela, M. O. Orlandi, E. Longo and M. S. Li, *CrystEngComm*, **14**, 853 (2012).