Hydrogen Absorption at a Low Temperature by MgH_2 after Reactive Mechanical Grinding

Myoung Youp Song^{1†}, Seong Ho Lee², Young Jun Kwak² and Hye Ryoung Park³

¹Division of Advanced Materials Engineering, Research Center of Advanced Materials Development, Engineering Research Institute, Chonbuk National University, 567 Baekje-daero Deokjin-gu, Jeonju 561-756, Korea

²Department of Materials Engineering, Graduate School, Chonbuk National University, 567 Baekje-daero Deokjin-gu, Jeonju 561-756, Korea

³Faculty of Applied Chemical Engineering, Chonnam National University, 77 Yongbong-ro Buk-gu, Gwangju 500-757, Korea

(Received January 9, 2014 : Received in revised form March 5, 2014 : Accepted March 5, 2014)

Abstract Pure MgH_2 was milled under a hydrogen atmosphere (reactive mechanical grinding, RMG). The hydrogen storage properties of the prepared samples were studied at a relatively low temperature of 423 K and were compared with those of pure Mg. The hydriding rate of the Mg was extremely low (0.0008 wt% H/min at $n = 4$), and the MgH_2 after RMG had higher hydriding rates than that of Mg at 423 K under 12 bar H_2 . The initial hydriding rate of MgH_2 after RMG at 423 K under 12 bar H_2 was the highest (0.08 wt% H/min) at $n = 2$. At $n = 2$, the MgH_2 after RMG absorbed 0.39 wt% H for 5 min, and 1.21 wt% H for 60 min at 423 K under 12 bar H_2 . At 573 K under 12 bar H_2 , the MgH_2 after RMG absorbed 4.86 wt% H for 5 min, and 5.52 wt% H for 60 min at $n = 2$. At 573 K and 423 K under 1.0 bar H_2 , the MgH_2 after RMG and the Mg did not release hydrogen. The decrease in particle size and creation of defects by reactive mechanical grinding are believed to have led to the increase in the hydriding rate of the MgH_2 after RMG at a relatively low temperature of 423 K.

Key words pure magnesium hydride, activation, hydriding rate, microstructure, X-ray diffraction.

1. Introduction

Magnesium has advantages as a hydrogen storage material from the viewpoints of hydrogen storage capacity, cost and reserves in the earth's crust. The hydrogen storage capacity of Mg is comparatively high (7.6 wt%) partly since it is a light element. However, its reaction rate with H_2 is very low¹⁾ since it is hard to be pulverized due to high ductility.

A lot of work to improve the hydriding and dehydriding rates of magnesium has been performed by alloying with magnesium metals^{2,3)} such as Cu,⁴⁾ Ni,^{5,6)} In,⁷⁾ Sn,⁸⁾ V,⁹⁾ and Ni and Y,¹⁰⁾ by synthesizing compounds such as CeMg_{12} ¹¹⁾ and $\text{Mg}_{76}\text{Ti}_{12}\text{Fe}_{12-x}\text{Ni}_x$ ($x = 4, 8$),¹²⁾ and by making composites such as Mg - 20 wt% Fe_{23}Y_8 .¹³⁾ Aminorroaya et al.¹⁴⁾ added Nb and multi-walled carbon nanotubes to Mg-Ni alloys, and Cho et al.¹⁵⁾ added transition metals to cast Mg-Ni alloys for the improvement of the reaction

rates of Mg with H_2 . Milanese et al.¹⁶⁾ mixed Ni and Cu with Mg, Tanguy et al.¹⁷⁾ mixed metal additives with magnesium, and Eisenberg et al.¹⁸⁾ plated nickel on the surface of magnesium to improve the hydriding-dehydriding kinetics of MgH_2 .

Mao et al.¹⁹⁾ investigated doping MgH_2 with NiCl_2 and CoCl_2 in an effort to develop MgH_2 with a low dehydriding temperature and fast sorption kinetics. Both the dehydrogenation temperature and the absorption/desorption kinetics were improved by adding either NiCl_2 or CoCl_2 , and a significant enhancement was obtained in the case of the NiCl_2 -doped sample.

Cermak and David²⁰⁾ studied separate catalytic effects of Ni, Mg_2Ni and Mg_2NiH_4 on the hydrogen desorption characteristics of MgH_2 . It was observed that the catalytic capacity of Mg_2NiH_4 was considerably higher than that of pure Ni and non-hydrated intermetallic Mg_2Ni .

By use of the first-principles density functional theory

[†]Corresponding author

E-Mail : songmy@jbnu.ac.kr (M. Y. Song, Chonbuk Nat'l Univ.)

© Materials Research Society of Korea, All rights reserved.

This is an Open-Access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/3.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

for a cluster model, the alloying effect of transition element M on the electronic structure of magnesium hydride, MgH_2 , was investigated by Chen et al.²¹⁾ They concluded that the chemical interaction between Mg and H may play a dominant role in the pure MgH_2 system. Such a strong interaction remained in the alloyed Mg(M)H_2 when the central Mg was replaced by an alloying element M. In view of the reasonably good agreement between the calculated M(or Mg)-H interactions and the enthalpies of formation for some pure dihydrides, they reported that 70% chemical(ionic plus covalent) interactions would appear to be ionic but the covalent interaction of an adjacent Mg to M with a H atom around it would be sensitive to the substitution of M.

The paper of Matović et al.²²⁾ dealt with non-isothermal kinetics models of hydrogen desorption from MgH_2 altered by ion bombardment and stressed the importance of the MgH_2 surface during its decomposition. The concentration and good dispersion of defects in near-surface region were important factors.

Song's review²³⁾ on the kinetic studies of the hydriding and dehydriding reactions of Mg reported that the hydriding and dehydriding reactions of Mg are nucleation-controlled under certain conditions and progress by a mechanism of nucleation and growth, and that the hydriding rates of Mg are controlled by the diffusion of hydrogen atoms through a growing Mg hydride layer.

The hydriding and dehydriding rates of magnesium can thus be increased by milling Mg or MgH_2 under hydrogen atmosphere(reactive mechanical grinding, RMG). Reactive mechanical grinding will decrease the particle size and create defects. Bobet et al.²⁴⁾ investigated the influence of RMG on the hydrogen storage properties of Mg-based mixtures. They reported that RMG increased the reactive surface area and created defects, leading to improvement in diffusion and nucleation.

In this work, pure MgH_2 was milled under hydrogen atmosphere. Hydrogen storage properties of the prepared samples were studied at a relatively low temperature of 423 K, and compared with those of pure Mg.

2. Experimental details

Pure MgH_2 powder(hydrogen storage grade, Aldrich) and pure Mg powder(−100 + 200 mesh, purity 99.6 %, Alfa Aesar) were used.

Reactive mechanical grinding was performed in a planetary ball mill(Planetary Mono Mill; Pulverisette 6, Fritsch). The pure MgH_2 (total weight = 8 g) was mixed in a hermetically sealed stainless steel container with 105 hardened steel balls(total weight = 360 g); the sample to ball weight ratio was 1/45. All sample handling was performed in a glove box under Ar in order to prevent

oxidation. The disc revolution speed was 400 rpm. The mill container(volume of 250 mL) was then filled with high purity hydrogen gas(~12 bar). The reactive mechanical grinding was performed for 2 h by repeating 15 min milling and 5 min rest. The mill container was refilled with hydrogen every two hours. These milling conditions were the optimum ones to improve hydriding and dehydriding rates of magnesium hydride in our previous work.²⁵⁾

The absorbed or desorbed hydrogen quantity was measured as a function of time by a volumetric method, using a Sievert's type hydriding and dehydriding apparatus described previously.²⁶⁾ At a given temperature, after hydriding reaction measurement under 12 bar H_2 for 1 h, dehydriding reaction measurement under 1.0 bar H_2 was performed for 1 h, and then the sample was dehydrided at 623 K in vacuum for 2 h. 0.5 g of the samples was used for these measurements. Samples after reactive mechanical grinding and those after hydriding-dehydriding cycling were characterized by X-ray diffraction(XRD) with Cu $\text{K}\alpha$ radiation, using a Rigaku D/MAX 2500 powder diffractometer. The microstructures of the samples after reactive mechanical grinding and after hydriding-dehydriding cycling were observed by a JSM-6400 scanning electron microscope(SEM) operated at 20 kV. ASAP2010(Accelerated Surface Area and Porosimetry analyzer, Micromeritics, USA) was used for analyzing the particle size distribution of the MgH_2 after RMG.

3. Results and Discussions

The amount of absorbed hydrogen, H_a , is expressed with respect to sample weight. Fig. 1 shows the variation of H_a versus t curve at 573 K under 12 bar H_2 with the number of cycles, n , for the MgH_2 after RMG. In the beginning, the hydriding rate is very high, and it be-

Fig. 1. Variation of H_a versus t curve at 573 K under 12 bar H_2 with the number of cycles, n , for the MgH_2 after RMG.

Table 1. Variation of the quantity of hydrogen absorbed by the MgH_2 after RMG at 573 K under 12 bar H_2 with time at $n = 1$ and at $n = 2$.

H_a (wt% H) at 573 K		
time (min)	$n = 1$	$n = 2$
0	0.00	0.00
5	4.86	4.86
10	5.23	5.22
30	5.42	5.45
60	5.51	5.52

Table 2. Variation of the quantity of hydrogen absorbed by the MgH_2 after RMG at 423 K under 12 bar H_2 with time at $n = 1$ and at $n = 2$.

H_a (wt% H) at 423 K		
time (min)	$n = 1$	$n = 2$
0	0.00	0.00
5	0.14	0.39
10	0.25	0.51
30	0.73	0.84
60	1.21	1.21

Fig. 2. Variation of H_a versus t curve at 423 K under 12 bar H_2 with the number of cycles for the Mg. **Fig. 3.** Variation of H_a versus t curve at 423 K under 12 bar H_2 with the number of cycles for the MgH_2 after RMG.

comes very low after 10 min. The H_a versus t curves at $n = 1-3$ are very similar. The H_a values for 5 min and 60 min increase from $n = 1$ to $n = 2$ and decrease from $n = 2$ to $n = 3$, showing that the activation of the MgH_2 after RMG was completed after the first hydriding-dehydriding cycle. At $n = 1$, the MgH_2 after RMG absorbs 4.86 wt% H for 5 min and 5.51 wt% H for 60 min. At $n = 2$, the

MgH_2 after RMG absorbs 4.86 wt% H for 5 min and 5.52 wt% H for 60 min. Table 1 presents the variation of the quantity of hydrogen absorbed by the MgH_2 after RMG at 573 K under 12 bar H_2 with time at $n = 1$ and at $n = 2$.

The variation of H_a versus t curve at 423 K under 12 bar H_2 with the number of cycles for the Mg is shown in Fig. 2. The hydriding rates of the Mg are extremely low. The Mg absorbs 0.05 wt% H for 60 min at $n = 4$, corresponding to a hydriding rate of 0.0008 wt% H/min.

Fig. 3 shows the variation of H_a versus t curve at 423 K under 12 bar H_2 with the number of cycles for the MgH_2 after RMG. The hydriding rates are not high, and the H_a values for 60 min are not large, either. However, the MgH_2 after RMG absorbs hydrogen at a relatively low temperature of 423 K. Roughly speaking, the initial hydriding rate and the H_a value for 60 min increase from $n = 1$ to $n = 2$ and decrease from $n = 2$ to $n = 4$. At $n = 1$, the MgH_2 after RMG absorbs 0.14 wt% H for 5 min and 1.21 wt% H for 60 min. At $n = 2$, the MgH_2 after RMG absorbs 0.39 wt% H for 5 min and 1.21 wt% H for 60 min. Table 2 presents the variation of the quantity of hydrogen absorbed by the MgH_2 after RMG at 423 K under 12 bar H_2 with time at $n = 1$ and at $n = 2$.

Fig. 2 and Fig. 3 show that the hydriding rate of the Mg is extremely low, absorbing 0.05 wt% H for 60 min at $n = 4$ (the initial hydriding rate 0.0008 wt% H/min at $n = 4$), and the MgH_2 after RMG has a higher initial hydriding rate (0.08 wt% H/min) than the Mg, absorbing 1.21 wt% H for 60 min at $n = 2$, at 423 K under 12 bar H_2 .

Fig. 4 shows the variations, with the number of cycles, of the initial hydriding rate and H_a for 60 min under 12 bar H_2 for the MgH_2 after RMG at 573 K and 423 K. The initial hydriding rates were obtained from the H_a values from 0 min to 5 min. The initial hydriding rates at 573 K are much higher than those at 423 K. The initial hydriding rate at 573 K remains almost constant and they are very similar from $n = 1$ to $n = 3$. But the initial hydriding rate at 423 K increases from $n = 1$ to $n = 2$ and decreases from $n = 2$ to $n = 4$. The values of H_a for 60 min at 573 K are much larger than those at 423 K. The value of H_a for 60 min at 573 K remains almost constant and

Fig. 4. Variations, with the number of cycles, of (a) the initial hydriding rate and (b) H_a for 60 min under 12 bar H_2 for the MgH_2 after RMG at 573 K and 423 K.

Fig. 5. SEM micrographs of the MgH_2 after RMG at different magnifications.

Fig. 6. SEM micrographs of the MgH_2 after RMG dehydrided at $n=5$ at different magnifications.

they are very similar from $n=1$ to $n=3$. But the value of H_a for 60 min at 423 K increases from $n=1$ to $n=2$ and decreases from $n=2$ to $n=4$. The initial hydriding rates of the MgH_2 after RMG at $n=2$ are 0.97 and 0.08 wt% H/min at 573 and 423 K, respectively. The values of H_a for 60 min of the MgH_2 after RMG at $n=2$ are 5.52 and 1.21 wt% H at 573 and 423 K, respectively.

At 573 K and 423 K under 1.0 bar H_2 , the MgH_2 after RMG and the Mg did not release hydrogen.

The XRD pattern of the MgH_2 after RMG showed that this sample contained β - MgH_2 , and small amounts of Mg, γ - MgH_2 , and MgO. β - MgH_2 is a low pressure form of MgH_2 that has a tetragonal structure. γ - MgH_2 is one of the high pressure forms of MgH_2 having an orthorhombic structure. This showed that γ - MgH_2 was formed during reactive mechanical grinding. The XRD pattern of the MgH_2 after RMG exhibited a quite strong background and broad peaks, indicating that the MgH_2 after RMG

Fig. 7. Particle size distribution of the MgH_2 after RMG.

was slightly amorphous.

Fig. 5 shows the SEM micrographs of the MgH_2 after RMG. The sample has small and large particles. The particle size is not homogeneous.

The SEM micrographs of the MgH_2 after RMG dehydrided at $n = 5$ are shown in Fig. 6. The particle size is not homogeneous. During hydriding reaction, the particles expand. The particles after hydriding-dehydriding cycling are larger than those after reactive mechanical grinding.

Fig. 7 shows the particle size distribution of the MgH_2 after RMG. The particle sizes are from 0 to 5 μm . The curve has two peaks at about 0.7 and 3.5 μm . The mean particle size is 1.39 μm .

The hydriding reaction of magnesium can be classified by the following: transfer of hydrogen molecules to the surface of Mg, chemisorption of H_2 molecules on the surface of Mg, transition of hydrogen atoms from the chemisorbed state to the absorbed state, and nucleation of magnesium hydride and growth. If a continuous layer of magnesium hydride is formed, diffusion of hydrogen atoms through a growing hydride layer occurs, and then phase transformation from α Mg-H solid solution to magnesium hydride takes place at the magnesium hydride- α Mg-H solid solution interface.

As mentioned above, the hydriding and dehydriding reactions of Mg are reportedly nucleation-controlled under certain conditions and the hydriding rates of Mg are controlled by the diffusion of hydrogen atoms through a growing Mg hydride layer.²³⁾

Reactive mechanical grinding is considered to decrease the particle size of magnesium hydride and create defects. The diminution in the particle size decreases the diffusion distances of hydrogen atoms, and the creation of defects facilitates nucleation. These effects are believed to have led to the increase in the hydriding rate of the MgH_2 after RMG at a relatively low temperature of 423 K.

On the other hand, the Mg has a small surface area and a few defects, leading to its low hydriding and dehydriding rates.

The reactive mechanical grinding of MgH_2 was performed in a planetary ball mill under the high purity hydrogen gas of about 12 bar at a disc revolution speed of 400 rpm for 2 h. The initial hydriding rate of the MgH_2 after RMG at 423 K under 12 bar H_2 was the highest (0.08 wt% H/min) at $n = 2$.

4. Conclusions

Pure MgH_2 was milled under hydrogen atmosphere. Hydrogen storage properties of the prepared samples were studied at a relatively low temperature of 423 K, and compared with those of pure Mg. The hydriding rate of the Mg was extremely low (0.0008 wt% H/min at $n = 4$), and the MgH_2 after RMG had higher hydriding rates than the Mg, at 423 K under 12 bar H_2 . At $n = 2$, the MgH_2 after RMG absorbed 0.39 wt% H for 5 min and 1.21 wt% H for 60 min at 423 K under 12 bar H_2 . The initial hydriding rate of the MgH_2 after RMG at 423 K under 12 bar H_2 was the highest (0.08 wt% H/min) at $n = 2$. At 573 K under 12 bar H_2 , the MgH_2 after RMG absorbed 4.86 wt% H for 5 min and 5.52 wt% H for 60 min at $n = 2$. At 573 K and 423 K under 1.0 bar H_2 , the MgH_2 after RMG and the Mg did not release hydrogen. The decrease in particle size and creation of defects by reactive mechanical grinding are believed to have led to the increase in the hydriding rate of the MgH_2 after RMG at a relatively low temperature of 423 K.

Acknowledgments

This research was supported by Basic Science Research Program through the National Research Foundation (NRF) of Korea funded by the Ministry of Education, Science and Technology (grant number 20110023566).

References

1. M. Y. Song, Y. J. Kwak, B. S. Lee, H. R. Park and B. G. Kim, *Kor. J. Met. Mater.*, **49**(12), 989 (2011).
2. S. H. Hong, S. N. Kwon, and M. Y. Song, *Kor. J. Met. Mater.*, **49**(4), 298 (2011).
3. K. I. Kim and T. W. Hong, *Kor. J. Met. Mater.*, **49**(3), 264 (2011).
4. J. J. Reilly and R. H. Wiswall, *Inorg. Chem.*, **6**(12), 2220 (1967).
5. J. J. Reilly and R. H. Wiswall Jr, *Inorg. Chem.*, **7**(11), 2254 (1968).
6. E. Akiba, K. Nomura, S. Ono and S. Suda, *Int. J. Hydrogen Energy*, **7**(10), 787 (1982).
7. M. H. Mintz, Z. Gavira and Z. Hadari, *J. Inorg. Nucl.*

- Chem., **40**(5), 765 (1978).
8. H. C. Zhong, H. Wang, L. Z. Ouyang and M. Zhu, *J. Alloys Compd.*, **509**(11), 4268 (2011).
 9. P. Pei, X. Song, J. Liu, A. Song, P. Zhang and G. Chen, *Int. J. Hydrogen Energy*, **37**(1), 984 (2012).
 10. Z. Li, X. Liu, L. Jiang and S. Wang, *Int. J. Hydrogen Energy*, **32**(12), 1869 (2007).
 11. J. M. Boulet and N. Gerard, *J. Less-Common Met.*, **89**(1), 151 (1983).
 12. M. Lucaci, Al. R. Biris, R. L. Orban, G. B. Sbarcea and V. Tsakiris, *J. Alloys Compd.*, **488**(1), 163 (2009).
 13. Z. Li, X. Liu, Z. Huang, L. Jiang and S. Wang, *Rare Metals*, **25**(6) (Supplement 1), 247 (2006).
 14. S. Aminorroaya, A. Ranjbar, Y. H. Cho, H. K. Liu and A. K. Dahle, *Int. J. Hydrogen Energy*, **36**(1), 571 (2011).
 15. Y. H. Cho, S. Aminorroaya, H. K. Liu and A. K. Dahle, *Int. J. Hydrogen Energy*, **36**(8), 4984 (2011).
 16. C. Milanese, A. Girella, G. Bruni, P. Cofrancesco, V. Berbenni, P. Matteazzi and A. Marini, *Intermetallics*, **18**(2), 203 (2010).
 17. B. Tanguy, J. L. Soubeyroux, M. Pezat, J. Portier and P. Hagenmuller, *Mater. Res. Bull.*, **11**(11), 1441 (1976).
 18. F. G. Eisenberg, D. A. Zagnoli and J. J. Sheridan III, *J. Less-Common Met.*, **74**(2), 323 (1980).
 19. J. Mao, Z. Guo, X. Yu, H. Liu, Z. Wu and J. Ni, *Int. J. Hydrogen Energy*, **35**(10), 4569 (2010).
 20. J. Cermak and B. David, *Int. J. Hydrogen Energy*, **36**(21), 13614 (2011).
 21. D. Chen, Y. M. Wang, L. Chen, S. Liu, C. X. Ma and L. B. Wang, *Acta Materialia*, **52**(2), 521 (2004).
 22. L. Matović, S. Kurko, Ž. Rašković-Lovre, R. Vujasin, I. Milanović, S. Milošević and J. Grbović Novaković, *Int. J. Hydrogen Energy*, **37**(8), 6727 (2012).
 23. M. Y. Song, S. H. Baek, J. -L. Bobet, H. R. Park, and B. G. Kim, *Met. Mater. Int.*, **19**(2), 237 (2013).
 24. J. -L. Bobet, B. Chevalier, M. Y. Song, B. Darriet, *J. Alloys Compd.*, **356-357**, 570 (2003).
 25. M. Y. Song, Y. J. Kwak, S. H. Lee, H. R. Park, and B. G. Kim, *Met. Mater. Int.*, **19**(4), 879 (2013).
 26. M. Y. Song, S. H. Baek, J. -L. Bobet, and S. H. Hong, *Int. J. Hydrogen Energy*, **35**(19), 10366 (2010).